

Title	Phosphorus monolayer doping (MLD) of silicon on insulator (SOI) substrates
Author(s)	Kennedy, Noel; Duffy, Ray; Eaton, Luke; Garvey, Shane; Connolly, James; Hatem, Chris; Holmes, Justin D.; Long, Brenda
Publication date	2018-08-06
Original citation	Kennedy, N., Duffy, R., Eaton, L., O'Connell, D., Monaghan, S., Garvey, S., Connolly, J., Hatem, C., Holmes, J. D. and Long, B. (2018) 'Phosphorus monolayer doping (MLD) of silicon on insulator (SOI) substrates', Beilstein Journal of Nanotechnology, 9, pp. 2106-2113. doi: 10.3762/bjnano.9.199
Type of publication	Article (peer-reviewed)
Link to publisher's version	https://www.beilstein-journals.org/bjnano/content/pdf/2190-4286-9-199.pdf http://dx.doi.org/10.3762/bjnano.9.199 Access to the full text of the published version may require a subscription.
Rights	© 2018 Kennedy et al.; licensee Beilstein-Institut. This is an Open Access article under the terms of the Creative Commons Attribution License (http://creativecommons.org/licenses/by/4.0). Please note that the reuse, redistribution and reproduction in particular requires that the authors and source are credited. The license is subject to the Beilstein Journal of Nanotechnology terms and conditions: (https://www.beilstein-journals.org/bjnano) The definitive version of this article is the electronic one which can be found at: doi:10.3762/bjnano.9.199 http://creativecommons.org/licenses/by/4.0
Item downloaded from	http://hdl.handle.net/10468/6686

Downloaded on 2019-02-22T10:01:58Z

Supporting Information

for

Phosphorus monolayer doping (MLD) of silicon on insulator (SOI) substrates

Noel Kennedy^{*1}, Ray Duffy², Luke Eaton¹, Dan O'Connell², Scott Monaghan², Shane Garvey², James Connolly³, Chris Hatem⁴, Justin D. Holmes^{1,5} and Brenda Long^{1,2}

Address: ¹School of Chemistry, University College Cork, Cork, Ireland; ²Tyndall National Institute, Lee Maltings, Cork, Ireland; ³Applied Materials, Lee Maltings, Cork, Ireland; ⁴Applied Materials, Gloucester, Massachusetts, USA and ⁵CRANN@AMBER, Trinity College Dublin, Dublin 2, Ireland

Email: Noel Kennedy* - 111456882@umail.ucc.ie

* Corresponding author

Additional experimental data

Table S1: Comprehensive Hall effect data acquired from 66 nm and 13 nm P-MLD-doped SOI substrates.

Sample:		66nm		13nm (1of2)	
Property	Units	Best DC	Best AC	Best DC	Best AC
Thickness	nm	66	66	13	13
2P-4P current	A	50n-500n	50n-500n	50n-500n	50n-500n
2P Ohmic	none	0.997798	0.998587	1	1
2P Ravg	ohm	200k	175k	11.0k	10.8k
4P F-value	none	1	1	1	1
4P Ravg	ohm	480	475	1.0k	1.0k
Rc estimate	ohm	199.5k	174.5k	10.0k	9.8k
4P ρ_s	ohm/sq.	2.18k	2.16k	4.57k	4.46k
4P ρ	ohm.cm	14.37m	14.23m	5.94m	5.80m
d/dt change?	none	N/A	Yes	N/A	Some, ~2%
4P SNR est.	none	>~60:1	>~62:1	>~730k:1	>~744:1
Hall current	A	500n	500n	500n	500n
Hall B-field	T T rms	1.7	1.24	1.7	1.24
Scan speed	none	N/A	Medium	N/A	Medium
Gain/Sense	dB/ μ V	N/A	0/500	N/A	0/500
Hall voltage	μ V	-25.03	16.92	-25.93	17.21
C. Type/%	none	N/100	N/100	N/100	N/100
Geo error?	none	No	No	No	No
Mobility μ H	cm ² /(V.s)	135.24	125.72	66.82	61.79
Sheet CC, ns	1/cm ²	2.12E+13	2.30E+13	2.05E+13	2.26E+13
CC, n	1/cm ³	3.21E+18	3.49E+18	1.57E+19	1.74E+19
Rhs	cm ² /C	2.94E+05	2.71E+05	3.05E+05	2.76E+05
Rh	cm ³ /C	1.94	1.79	0.397	0.358
Hall SNR est.	none	>~4:1	>~7:1	>~52:1	>~30:1
Phase	Degrees	N/A	-179.8	N/A	179.9




Figure S1: ECV profiles of the P-MLD on bulk silicon annealing time variation experiment. Samples were capped with 50 nm sputtered SiO₂ and annealed at 1050 °C for time periods of 5 s (green), 10 s (blue), and 100 s (red). The incorporated dose value after the 100 s annealing is $1.28 \times 10^{14} \text{ cm}^{-2}$, which is close to what would be expected from a monolayer of allyldiphenylphosphine dopant molecules.




Figure S2: ECV profiles of P-MLD on bulk silicon annealing temperature variation experiment. Samples were capped with 50 nm sputtered SiO₂ and annealed at 950 °C (blue), 1000 °C (red), 1050 °C (green) and 1100 °C (orange) for a time period of 5 s.