

**UCC Library and UCC researchers have made this item openly available.
 Please [let us know](#) how this has helped you. Thanks!**

Title	Defect chemistry and vacancy concentration of luminescent europium doped ceria nanoparticles by solvothermal method
Author(s)	Thorat, Atul V.; Ghoshal, Tandra; Carolan, Patrick B.; Holmes, Justin D.; Morris, Michael A.
Publication date	2014-04-28
Original citation	Thorat, A. V., Ghoshal, T., Carolan, P., Holmes, J. D. and Morris, M. A. (2014) 'Defect Chemistry and Vacancy Concentration of Luminescent Europium Doped Ceria Nanoparticles by the Solvothermal Method', The Journal of Physical Chemistry C, 118(20), pp. 10700-10710. doi: 10.1021/jp410213n
Type of publication	Article (peer-reviewed)
Link to publisher's version	https://pubs.acs.org/doi/10.1021/jp410213n http://dx.doi.org/10.1021/jp410213n Access to the full text of the published version may require a subscription.
Rights	© 2014 American Chemical Society. This document is the Accepted Manuscript version of a Published Work that appeared in final form in Journal of Physical Chemistry C , copyright © American Chemical Society after peer review and technical editing by the publisher. To access the final edited and published work see https://pubs.acs.org/doi/10.1021/jp410213n
Item downloaded from	http://hdl.handle.net/10468/6788

Downloaded on 2022-08-10T20:33:07Z

Supporting Information for:

Defect chemistry and vacancy concentration of luminescent europium doped ceria nanoparticles by solvothermal method

Atul V. Thorat,^{a,b,c} Tandra Ghoshal,^{a,b,c} Patrick Carolan,^b Justin D. Holmes,^{a,b,c} and Michael
A. Morris^{*,a,b,c}

^a Materials research group, Department of Chemistry, University College Cork, Cork, Ireland

^b Tyndall National Institute, University College Cork, Cork, Ireland

^c Centre for Research on Adaptive Nanostructures and Nanodevices (CRANN), Trinity
College Dublin, Dublin, Ireland

[*] Corresponding Author: Prof. Michael A. Morris

E-mail: m.morris@ucc.ie

Tel: + 353 21 490 2180

Fax: +353 21 427 4097

Total external reflection X-ray fluorescence (TXRF): TXRF was used to confirm the metal cation ratio of the synthesised powdered ceria.




Figure S-1. Typical TXRF graphs of europium doped ceria nanoparticles showing line positions. (a) CEEU7.6 (b) CEEU19.6

Particle size distribution of undoped and doped ceria nanoparticles:

Figure S-2 shows the particle size distribution for the undoped, 0.8 % and 13.9 % Eu doped ceria samples calculated from TEM images. The plot shows ± 0.4 nm disparity in the particles sizes.






Figure S-2. Particle size distribution of (a) undoped (b) 0.8 % Eu doped (c) 13.9 % Eu doped ceria samples.

EDAX mapping by STEM:




Figure S-3. Ce-L, Eu-L, O-K mapping of ceria cluster of CEEU7.6 by STEM. (a) aberration-corrected STEM image of ceria cluster (b) superimposed display of the elemental mapping on ceria cluster.

The large scale mapping on ceria samples was taken by scanning transmission electron microscopy (STEM) to demonstrate the distribution of doped Europium in ceria nanoparticles. Figure S-3 shows the aberration-corrected STEM image, Ce-L, Eu-L, O-K elemental mapping of ceria cluster of CEEU7.6 sample. The elemental maps exhibit the

presence of Eu, Ce and O throughout the cluster. This result indicates that the europium is uniformly distributed in ceria and not present as a free species within the powdered sample.