

Title	Supercritical carbon dioxide versus toluene as reaction media in silica functionalisation: Synthesis and characterisation of bonded aminopropyl silica intermediate
Authors	Ashu-Arrah, Benjamin A.;Glennon, Jeremy D.
Publication date	2017-04-14
Original Citation	Ashu-Arrah, B. A. and Glennon, J. D. (2017) 'Supercritical carbon dioxide versus toluene as reaction media in silica functionalisation: Synthesis and characterisation of bonded aminopropyl silica intermediate', Journal of Chromatography A, 1501, pp. 18-25. doi:10.1016/j.chroma.2017.04.030
Type of publication	Article (peer-reviewed)
Link to publisher's version	10.1016/j.chroma.2017.04.030
Rights	© 2017 Elsevier. This manuscript version is made available under the CC-BY-NC-ND 4.0 license http://creativecommons.org/ licenses/by-nc-nd/4.0/ - http://creativecommons.org/licenses/by- nc-nd/4.0/
Download date	2025-07-06 16:12:06
Item downloaded from	https://hdl.handle.net/10468/3955



University College Cork, Ireland Coláiste na hOllscoile Corcaigh

Accepted Manuscript

Title: Supercritical carbon dioxide versus toluene as reaction media in silica functionalisation: Synthesis and characterisation of bonded aminopropyl silica intermediate



Authors: Benjamin A. Ashu-Arrah, Jeremy D. Glennon

PII:S0021-9673(17)30583-6DOI:http://dx.doi.org/doi:10.1016/j.chroma.2017.04.030Reference:CHROMA 358464To appear in:Journal of Chromatography AReceived date:29-11-2016Revised date:29-3-2017Accepted date:12-4-2017

Please cite this article as: Benjamin A.Ashu-Arrah, Jeremy D.Glennon, Supercritical carbon dioxide versus toluene as reaction media in silica functionalisation: Synthesis and characterisation of bonded aminopropyl silica intermediate, Journal of Chromatography Ahttp://dx.doi.org/10.1016/j.chroma.2017.04.030

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Supercritical carbon dioxide versus toluene as reaction media in silica functionalisation: Synthesis and characterisation of bonded aminopropyl silica intermediate.

Benjamin A. Ashu-Arrah, Jeremy D. Glennon

Innovative Chromatography Group, Irish Separation Science Cluster (ISSC), Department of Chemistry, and the Analytical and Biological Chemistry Research Facility (ABCRF), University College Cork, Ireland.

Highlights

- Supercritical CO₂ a competitive alternative reaction medium to organic solvents.
- Synthesis of aminopropyl bonded silica (APS) intermediate for LC applications.
- Higher %C loading/conversion efficiency for APS using supercritical-CO₂ protocol compared to toluene.
- Change in surface charge of silica from negative to positive for APS, confirmed by zeta potential measurements.

Abstract

This research reports supercritical carbon dioxide versus toluene as reaction media in silica functionalisation for use in liquid chromatography. Bonded aminopropyl silica (APS) intermediates were prepared when porous silica particles (Exsil-pure, 3µm) were reacted with 3aminopropyltriethoxysilane (3-APTES) or N,N-dimethylaminopropyltrimethoxysilane (DMAPTMS) using supercritical carbon dioxide (sc- CO_2) and toluene as reaction media. Covalent bonding to silica was confirmed using elemental microanalysis (CHN), thermogravimetric analysis (TGA), zeta potential (ξ) , diffuse reflectance infrared Fourier transform (DRIFT) spectroscopy, scanning electron microscopy (SEM) and solid-state nuclear magnetic resonance (CP/MAS NMR) spectroscopy. The results demonstrate that under sc-CO₂ conditions of 100°C/414 bar in a substantial reduced time of 3 h, the surface coverage of APS (evaluated from %C obtained from elemental analysis) prepared with APTES (%C: 8.03, 5.26 μ mol/m⁻²) or DMAPTES (%C: 5.12, 4.58 μ mol/m²) is somewhat higher when compared to organic based reactions under reflux in toluene at a temperature of 110°C in 24 h with APTES (%C: 7.33, 4.71µmol/m²) and DMAPTMS (%C: 4.93, 4.38µmol/m²). Zeta potential measurements revealed a change in electrostatic surface charge from negative values for bare Exsil-pure silica to positive for functionalised APS materials indicating successful immobilization of the aminosilane onto the surface of silica.

Keywords: Chemical functionalisation; Supercritical CO₂; Aminopropyl bonded silica (APS); bifunctional bonding; Surface coverage/conversion efficiency.

1. Introduction

The chemical functionalisation of silica particles and surfaces is an active research area owing to flexibility in pore structure and universal acceptance of these materials in a variety of applications compared to other metal oxides such as alumina and titania [1]. Silica particle surface area, accessibility and pore size has a direct influence on percentage carbon loading and functionalisation efficiency. The higher the surface area and pore access, the more available sites for ligand immobilization. The type and functionality of silane ligand (chloro, or alkoxy) used in the generation of silica bonded phases determines the reaction mechanism and the corresponding type and

quantitative amount of surface bound species. Solid state NMR spectroscopy is particularly valuable in elucidating the surface bonded species. Reactions involving monofunctional silanes with silica provide a ²⁹Si CP/MAS NMR single resonance peak centered at +13ppm. Multifunctional silanes (di-,tri) will provide more than one linkage of siloxane attachment to a highly crosslinked siloxanes between silanes and silica surface silanols [2]. ²⁹Si CP/MAS NMR spectra of di-functional modified silica surface will yield resonances between -4ppm and -22ppm of the silane, and trifunctional modified silica will have resonances of T¹ (-46 ppm), T^{1'} (-50ppm) and T² (-56ppm), T³ + T^{3'} (-59ppm) in addition to signals at -92ppm (Q², geminal silanols), -101ppm (Q³, free silanols) and -110ppm (Q⁴, siloxanes) [2].

Amino functionalised silicas, if not used directly as the stationary phase, are often used as intermediates for further modification of bonded stationary phases in chromatography [3, 4]. Other uses of aminopropyl silica (APS) cited in the literature are in the area of catalysis [5, 6], drug delivery [7], solid-phase extraction [8], chemical sensors[9] and in nanomaterials [10, 11].

Aminopropyltriethoxysilane (APTES) is of particular importance due to its bi-directional character, the ethoxy groups reacting with hydroxyl groups on the surface of silica forming siloxanes (Si-O-Si) linkages, with the amino group extending from the surface as a linker for the attachment of other ligands or molecules via nucleophilic substitution reaction. The amino group is further reacted by formation of amide or amine, and by alkylation in addition with nucleophilic aromatic substitution of suitable activated rings. The formation of amides can be achieved with acid chlorides or anhydrides. The directional property has led to the popularity of APTES as a silanating ligand. Albert *et al.* have described the chemical species of APS gel formed with APTES as ligand [12], while Tripp and White examined the nature of APS species by reacting silica with the mono-alkoxysilane, aminopropyldimethylethoxysilane (APDMES)[13].

Current methods of preparing APS intermediate phase primarily involve the use of conventional organic solvents, requiring disposal or recycling. For example, Erden *et al.* [8] activated silica with acetic acid for 1h, then proceeded to reflux with APTES in toluene for 24 h. Ray *et al.* [3] used 24 h to immobilized APTMS onto silica surface under reflux. In both examples, additional organic solvents were employed for purification procedures. Alternative functionalisation strategies such as solvent-free vapour phase and supercritical fluid silanisation that avoid organic solvents at high temperature would be desirable. Solvent-free vapour uses dry argon or nitrogen while supercritical fluid functionalisation can utilise sc-CO₂ as the reaction medium. However, the former can require purification/drying of functionalised materials [14, 15] involving the use of organic solvents. Materials functionalised in sc-CO₂ can be conveniently flushed with sc-CO₂ after reaction is complete [16, 17, 18,

19, 20, 21, 22] and the medium constitutes a more benign/efficient method of silanisation compared to solvent-free vapour protocol and conventional organic solvent based methods. These features can allow direct introduction of the functionalised material into a spectroscopic or chromatographic system without a further purification step [19, 20, 23]. Conventional based methods of functionalising silica can span several hours or even days at higher temperatures [3, 8]. Moreover, organic based synthetic methods are often prone to polymerization [24, 25] leading to higher carbon loading than expected.

Cao *et al.* studied reactions of organosilanes with silica surfaces in carbon dioxide [26]. Robson and co-workers prepared/endcapped silica bonded phase in sc-CO₂ [24], while Yarita *et al.* endcapped an octadecyl silica (ODS) previously prepared in organic solvent using sc-CO₂ as a silylation medium [27]. Ashu-Arrah *et al.* prepared bonded mercaptopropyl silica (MPS) [17], silica hydride (Si-H) intermediates [16] and phenyl and pentafluorophenyl silica phases [18, 19] using sc-CO₂ as the reaction medium.

Furthermore, Cao *et al.* [26] and Tripp and Combes [28] demonstrated that sc-CO₂ absorbed moisture from silica while performing silanisation thus acting as a desiccant, a feature which further differentiates sc-CO₂ from organic solvents. Ashu-Arrah *et al.*[16] and McCool and Tripp [28] observed that inaccessible silica silanols are accessible in sc-CO₂. Tripp and co-workers investigated the reaction of silica with organosilanes in sc-CO₂ using infrared spectroscopy [29, 30] while Gu and Tripp highlighted the effectiveness of silica functionalisation in sc-CO₂ by studying the reaction of silanes with metal oxides such as titania and alumina [31].

Ashu-Arrah *et al.* demonstrated superior surface coverage for sc-CO₂ generated silica hydride intermediate (using triethoxysilane, TES and dimethylmethoxysilane, DMMS) compared to conventional organic solvent based method [16]. The relatively higher surface coverage of SiH from TES compared to DMMS generated in sc-CO₂ is attributed to the trialkoxy moiety of the TES that favours siloxane crosslinkage, forming polymeric surface attachments to yield a higher ligand density than the monomeric DMMS ligand. Furthermore, silica hydride (SiH) conversion efficiency (estimated from ²⁹Si CP/MAS NMR analysis) of ca. 42.4% achieved for SiH prepared from DMMS using sc-CO₂ is superior to a 33.3% efficiency obtained in dioxane [16]. In this research, the authors examine the preparation of bonded aminopropyl silica (APS) intermediate under supercritical CO₂ conditions and compare the results with APS prepared using toluene as reaction medium. It has been demonstrated that polymeric C₁₈ bonded stationary phases prepared using different synthetic route have different chromatographic properties [32]. The extend of bonding of APTES and DMAPTMS onto the silica surface was examined by elemental microanalysis (CHN), thermo-gravimetric analysis (TGA), zeta

potential (ξ), scanning electron microscopy (SEM), diffuse reflectance infrared Fourier transform (DRIFT) spectroscopy and where available solid-state nuclear magnetic resonance (²⁹Si and ¹³C CP/MAS NMR) spectroscopy.

2. Experimental

2.1. Materials

Exsil-Pure porous silica (3μ m, $223m^2/g$, 120Å) was purchased from Alltech/Exmere (Lancashire, UK), while 3-aminopropyltriethoxysilane (3-APTES), N,N-dimethyl aminopropyltrimethoxysilane (DMAPTMS), triethylamine, 99% (TEA), acetonitrile, methanol (Chromosolv HPLC grade) and anhydrous toluene (99.8% analytical grade) were obtained from Sigma-Aldrich (Tallaght-Dublin, Ireland). All water was distilled and ionised on a Milli-Q water purification system (Millipore, Milford, Mass, USA) to a resistivity of 18.2 M Ω .cm. CO₂ supplied in cylinder was obtained from Irish Oxygen (Cork, Ireland) with > 99.9% CO₂ purity, a moisture content < 50 ppmv and < 10 ppmv methanol. All reagents were used as supplied except porous Exsil-Pure silica particles that were pre-treated by drying in an oven at 120°C overnight to remove surface bound moisture. These trace amounts of water and methanol present in the CO₂ are too low to influence the critical parameter settings chosen in this work to maintain supercritical conditions.

2.2. Instrumentation

Reaction in supercritical CO₂ was carried out using a stainless steel pressure cell with a total volume of 25ml, serial no 120773-4 fitted with 0.625 sapphire windows at either end of the cell, coupled with an Isco model 260D syringe pump obtained from Thartech Inc. (USA) used to establish and maintain CO₂ pressure. Temperature was controlled within \pm 1°C using an electrical heating tape monitored with a K thermocouple (Type:NiCr-Ni) placed in the reaction cell. The K thermocouple was purchased from Sigma-Aldrich (Dublin, Ireland). Gentle agitation of the cell content was accomplished by stirring with a Teflon coated magnetic stirrer bar in the cell and a magnetic stirrer plate underneath the cell. The magnetic stirring plate (Midi-MR 1 digital IKAMAG) was purchased from Ika Werke Gmbh & Co. KG (Germany).

2.3. Synthetic protocol for bonded aminopropyl silica (APS) stationary phase

2.3.1. Synthesis of aminopropyl silica intermediate in sc-CO₂

The procedures for the supercritical CO₂ functionalisation of silica intermediates [16, 17] and stationary phases[18, 19] has been described previously. Thus for 1.0g of dried porous silica, 1.2g of 3-APTES or DMAPTMS was used. Porous silica (1.0g) and 1.2g of APTES or DMAPTMS are charged into

a 25mL stainless steel reaction cell containing a magnetic stirring bar. The cell was sealed and wrapped with an electrical heating tape and place right on top of the magnetic stirrer. The magnetic stirrer was switched on to ensure gentle agitation of the cell contents (600 ± 2 rpm), which was visually verified by looking through the sapphire windows at either end of the reaction cell. The temperature of the reaction cell was raised beyond the critical temperature of CO₂ (31.2°C) when above the critical pressure. Once the temperature of the reaction cell was above the critical temperature of CO2 (31.2°C), all inlet valves were opened and pressurized CO₂ allowed to flow into the reaction cell under constant static conditions at 100°C, to maintain 414 bar for 3 h [16]. Following this reaction time of 3 h, the magnetic stirrer plate was switched off to allow the cell content to settle for ~20 min, followed by dynamic extraction for 30 min with ca.120mL of fresh sc-CO₂ flushed through the cell at a rate of ca. 8mL/min at constant conditions of 100°C and 414 bar. The cell was then depressurized, vented, cooled, opened and the bonded aminopropyl silica (APS) phase removed as a white flowing powder. The APS phases were oven dried (thermal or post-curing) overnight at 120°C as this is regarded as a final strengthening of the already immobilized silane species by condensation [33]. The supercritical CO₂ generated APS was labelled as sc-APS to differentiate from the org-APS synthesis in organic based method described below with toluene as solvent.

2.3.2. Synthesis of aminopropyl silica intermediate in toluene

To compare aminopropyl silica prepared in sc-CO₂ with conventional organic solvent based method, reaction in toluene was carried out in a 2-neck 100mL round bottom flask equipped with a reflux condenser. 1.0g of pre-dried (overnight oven drying at 120°C) porous silica was place in a 2-neck 100mL round flask with 10ml of anhydrous toluene as solvent, a magnetic stirring bar and 500µL of deionised water, stirred and heated for 10 min at 110°C under reflux. Then 1.2g of APTES or DMAPTMS and ~1% TEA (as catalyst) was added quickly and the mixture was maintained under refluxed for 24 h at 110°C under N₂ atmosphere. The content of the 2-neck 100mL round bottom flask was cooled at room temperature, and separated by vacuum filtration. The bonded aminopropyl silica (APS) phases were washed with 10mL of anhydrous toluene (three times) and rinsed with 10mL of methanol (three times). The resulting white powder of APS was oven dried overnight at 120°C and labelled as org-APS to differentiate from sc-APS.

2.4. Characterisation of bonded APS generated in $sc-CO_2$ and toluene

2.4.1. Percentage carbon

Elemental analysis of bonded APS was performed using a CE 440 elemental analyzer fully automated (Exeter Analytical Inc., North Chelmsford, Mass, USA) with thermal conductivity detection at the Microanalytical Laboratory, Chemistry Department, UCC (Cork, Ireland).

2.4.2. Thermogravimetric analysis

Thermogravimetric analysis (TGA) experiments were performed on a Star^e TGA/ DSC instrument, from Mettler-Toledo AG, Switzerland, over a temperature range from 30-900°C at a heating rate of 40°C/min under a nitrogen flow rate of ~30 mL/min on an alumina 70µL pan. 5-10mg of bonded APS phases were placed on a pre-tared alumina pan and the weight recorded. The samples were heated using a linear gradient under an inert atmosphere of nitrogen. Data was analysed using Star^e Excellence software.

2.4.3. Zeta potential (ξ) analysis

The zeta potential measurement was performed using a Zetasizer nano ZS model: ZEN3600 and serial number: MAL1030324, equipped with a MPT-2 multipurpose titrator operated using a DTS (nano) software ver.5.10 (Malvern Instruments, Worcestershire UK). 0.01% (w/w) (recommended for in-house zeta measurement) or ~0.001g samples were dispersed in 10 mL methanol and acetonitrile, and sonicated in a water bath for 12 min. Measurement were performed immediately after removing the suspension from the bath. A zeta dip cell was filled with samples and data analysed using a DTS (nano) software ver.5.10.

2.4.4. Scanning electron microscopy (SEM)

The external surface morphology of bonded APS phase and bare Exsil-pure silica particles were performed on a JSM-5510 SEM (FEI Company Europe) at 20 kV at the Bioscience Institute, University College Cork, Ireland.

2.4.5. Diffuse reflectance infrared Fourier transform (DRIFT) spectroscopy

DRIFT spectra of APS and bare Exsil-pure silica were performed on a Perkin-Elmer Spectrum Two FT-IR spectrometer (Chalfont Road, UK) with a FT-IR attachment (Pike Technologies, USA). Pre-dried KBr was ground to a fine powder using a mortar and pestle. A sample holder (width: 6 mm; depth: 2 mm) was filled with KBr, the surface levelled and subsequently used to record the background spectra. Bonded APS phase was then mixed with KBr at a ratio of 1:30, and further ground to a fine powder and a sample holder was filled and the surface levelled. All spectra were run from 4000cm⁻¹ to 400 cm⁻¹ at a scan rate of 16s⁻¹ and a resolution of 4 cm⁻¹.

2.4.6. Solid-state nuclear magnetic resonance spectroscopy

²⁹Si and ¹³C NMR spectroscopy measurements were performed at the Institute of Organic Chemistry, Tübingen, Germany, on on Bruker ASX 300 and DSX 200 spectrometers (Bruker, Rheinstetten, Germany) using cross polarization and magic-angle spinning (CP/MAS). The ¹³C CP/MAS and ²⁹Si CP/MAS NMR were recorded at 75.5MHz and at 59.6MHz respectively, with a contact time of 3 ms for ¹³C and 5 ms for the ²⁹Si nucleus, and a recycle delay time of 1s. Representative samples of ~250 mg were spun at 4 KHz using 7 mm double bearing ZnO_2 rotors (for ¹³C: ~80 mg in 4 mm rotors at a spinning rate of 10 kHz). The line broadening used was about 30Hz and the spectra width was about 20 kHz. All chemical shifts were referenced to trimethylsilyl ester of octameric silica (Q₈M₈) and glycine respectively. Spectrum processing was performed using Bruker TOPSPIN 2.0 software.

3. Results and Discussion

3.1. Elemental analysis, surface coverage and conversion efficiencies

Surface coverage and %C loading are reliable means of assessing the extent of a functionalisation method [1, 34]. As illustrated in Table 1, the observed increases in the CHN values for APS prepared in sc-CO₂ and toluene as reaction media compared with non-functionalised Exsil silica (%C: 0.02, %H: 0.32) are evidence of successful functionalisation of silica with APTES and DMAPTMS. The C/N value of sc-APS (i.e. C/N: 3.34 using APTES and 4.57 using DMAPTMS) is found to be greater than the theoretical value of the 3-amino propyl group but lower in the case of org-APS (i.e. C/N: 2.92 and 3.92) indicating extensive hydrolysis of the ethoxy and methoxy groups of APTES and DMAPTMS during the silanisation process.

Table 1. Elemental analysis values of APS intermediate prepared from 3-APTES and N, N-DMAPTMS) using sc-CO₂ (100°C/414 bar/3 h) and toluene (110°C/24 h) as reaction medium.

- ^a Reference: Erdem *et al*.[8]
- ^b Reference: Ray *et al*.[3]
- ^c Reference: [4]
- -, Value not available

The surface coverages of bonded APS intermediate was calculated using %C derived from elemental analysis, assuming bifunctional attachment and applying Barendsen-de-Galan equation [34, 35, 36]. A surface coverage of $5.26\mu mol/m^2$ (%C: 8.03) for APS prepared with APTES and DMAPTMS ($4.58\mu mol/m^2$, %C: 5.12) using sc-CO₂ corresponding to a conversion efficiency of 65.8% and 57.3% respectively of surface silanols based on a silanol concentration of $8.0 \pm 1.0\mu mol/m^2$ of bare silica. These values are higher than $4.71\mu mol/m^2$, APTES (%C: 7.33) and $4.38\mu mol/m^2$, DMAPTMS (%C: 4.93) corresponding to a conversion efficiency of 58.9% and 54.8% respectively obtained in toluene using

same silica type at a reaction temperature of 110° C for 24 h (Table 2). These results are in good agreement with C/N values, which is attributed to extensive hydrolysis of the ethoxy and methoxy groups of APTES and DMAPTMS in addition to subsequent silanol condensation or cross-linking reaction, coupled with the enhanced mass transfer kinetics (lower viscosity and high diffusivity) and solvating power (density) of sc-CO₂ enabling aminosilane to penetrate silica silanols and pores that are inaccessible in organic solvent [16, 28]. As illustrated in Table 2, the surface coverages of APS prepared in this research with APTES ligand (5.26µmol/m² using sc-CO₂ and 4.71µmol/m² in toluene) is higher than 4.67µmol/m² reported by Buszewski *et al.* [37] but somewhat lower than 6.74µmol/m² reported by Ray *et al.* [3]. The surface coverage of APS from DMAPTMS (4.58µmol/m² in sc-CO₂, and 4.38µmol/m² in toluene) is higher than 2.8µmol/m² reported by Bocian *et al.*[4]. Differences due to the use of silica with different physiochemical properties from different manufacturer, synthetic route, reaction solvents and aminosilane type are evident as highlighted in Table 2. For example, Buszewski *et al.* used Kromasil silica (100Å, 5µm, 310m²/g), Ray *et al.* used APTMS and Kromasil silica (100Å, 5µm, 313m²/g).

Table 2. Surface coverages of APS prepared with APTES and DMAPTMS using sc-CO₂ and toluene as reaction medium.

^a Surface coverage calculated based on de Galan equation: $\alpha(\mu mol/m^{-2}) = \frac{10^6 \times \%C}{S_{BET}(100Cn_c - \%CM_r)}$

^b Reference: [37]

^c Reference: [3]

^d Reference: [4]

3.2. Thermogravimetric analysis (TGA)

The TGA weight loss observed from 220 to 880°C range (Fig. 1) corresponds to the decomposition of the chemically immobilized aminopropyl groups attached on the surface of silica. As illustrated in Fig.1A, a weight loss of 12% and 7% at 490-500°C correspond to the decomposition of aminopropyl groups (i.e. APTES) of APS using sc-CO₂ and toluene respectively as reaction medium. TGA of APS prepared with DMAPTES in toluene shows a weight loss of 10% at 500°C (Fig. 1B). The increase TGA weight loss of 12% observed for APS prepared in sc-CO₂ clearly indicate an increased or strengthening

of bound aminopropyl groups following thermal treatment, which is attributed to the hydrolysis of the unreacted ethoxy groups of APTES directly with residual silanols and Si–O–Si linkages resulting in structural rearrangement of chemically bound aminopropyl groups. A small TGA weight loss 2-3% at 100°C corresponds to adsorbed moisture while weight loss at temperature above 650°C is attributed to the condensation of surface silanols liberating siloxanes and water. While TGA shows the thermal decomposition, the derivative (DTA) shows how rapid or slow the rate of decomposition in occurring, and is used to identify the desorption of different species [19].

Fig. 1A. TGA overlay with varying loading of aminopropyl groups of bonded APS intermediate phase prepared with 3-APTES using sc-CO₂ and toluene as reaction medium.

Fig. 1B. TGA/DTA of bonded APS intermediate phase prepared with DMAPTMS in toluene showing 3 distinct decomposition steps.

3.3. Zeta potential (ξ) analysis

Zeta potential measurements were performed four times each for bare silica and bonded APS intermediate phase and calculated average presented. As illustrated in Table 3, the negative zeta potential values (at pH 7-8) observed on bare silica is attributed to surface charges from silanol groups in the dissociated form (SiO⁻).

Table 3. Zeta Potentials (mV) for Exsil-pure silica and functionalized APS prepared fromAPTES

And these values are more negative in acetonitrile than in methanol partly due to the physiochemical properties of the dispersants (Table 4). A change in electrostatic charges from negative to positive for bonded APS confirmed successful immobilization of 3-APTES onto the surface of silica, and is consistent with cited results in the literature [10]. The more positive ξ values observed for supercritical CO₂ generated APS intermediate phase (sc-APS) compared to organic solvent based method in both methanol and acetonitrile indicate greater amino groups (-NH₃⁺) immobilization on the surface of silica as supported with higher carbon loading/surface coverages (Table 1 and 2). The difference in positive zeta potentials observed in methanol and acetonitrile is likely due to differences in dipole moment as shown in Table 4 coupled with differences in solvation of bonded APS. The high zeta potentials thus indicate that the APS particles have a strong surface charge and the repulsive force between particles is less susceptible to aggregation (also confirmed by SEM, Fig. 2) and therefore more stable. This

stability is in good agreement with TGA (Fig. 1) as the organic groups do not detach from the surface of silica at temperature lower than ~ 490 to 500°C.

Table 4. Physicochemical properties of methanol and acetonitrile used in zeta potential analysis at $25^{\circ}C^{a}$

^a Data from DTS (nano) software ver.510 ^b Reference:[38]

3.4. Scanning electron microscopy (SEM)

Examinations of the surface morphology of bonded APS intermediate phase prepared in $sc-CO_2$ and toluene by SEM (Fig. 2) clearly shows no evidence of aggregation.

Fig. 2. SEM micrographs of bare silica and APS phase generated from APTES using sc-CO₂ and toluene as reaction medium.

3.5. Diffuse reflectance infrared fourier transform (DRIFT) spectroscopy

DRIFT analysis clearly confirms the immobilization of 3-APTES onto the surface of silica (Fig.3) through comparing the spectra of bare silica and supercritical CO₂ generated APS (sc-APS). The appearance of new peaks at 3300cm⁻¹, 2932cm⁻¹, 2877cm⁻¹, 1557cm⁻¹ and 1327 cm⁻¹ are evident corresponding to the aminopropyl characteristic vibrations. As illustrated in Fig.3, the adsorption peaks of CH₂ at 2932cm⁻¹ and 2877cm⁻¹ is due to the propyl alkyl chain of 3-APTES. The intense peak at 1557cm⁻¹ is attributed to the bending vibrations of amino groups (NH₂), and the broad N-H band at 3300cm⁻¹ is due to asymmetric/symmetric stretching of hydrogen bonded NH₂ groups. The low intensity peak at 1327cm⁻¹ is assigned to the C-N stretching vibration. A similar spectrum (not shown here) was also obtained for APS prepared in toluene.

Fig. 3. DRIFT spectra of APS (APTES) generated in sc-CO₂ at conditions of 100°C/414bar/3 h.

Moreover, the spectrum of the sc-APS revealed a decreased in the intensity of the peak at 3661cm⁻¹ attributed to the single/geminal hydroxyl and hydrogen hydroxyl (O–H), compared to a broad peak at 3669-3648cm⁻¹ in the case of bare silica. The peak at 2338cm⁻¹ is attributed to residual adsorbed CO₂ on the surface of silica due to the use of sc-CO₂ as solvent, consistent with cited results in the literature

[17]. The band at 1650cm⁻¹ for both bare silica and modified APS is ascribed to physisorbed water, and/or bending vibration of water, while the strong signals observed at 1114-1013cm⁻¹ and 803cm⁻¹ are due to Si–O–Si vibrations [16, 17].

3.6. Solid-state nuclear magnetic resonance spectroscopy

The ²⁹Si CP/MAS spectrum of bonded aminopropyl silica (APS) stationary phase prepared with DMAPTMS in sc-CO₂ shows resonances at -66ppm and -69ppm assigned to T² and T³ species respectively attributed to covalent bonding of ligand onto the surface of silica. The signals at -101ppm and -110ppm are associated with vicinal or free silanols (Q³) and siloxanes (Q⁴) typical of native silica [2] respectively. The absent of the monodentate species (T¹) and the most reactive geminal silanols (Q², which normally appeared at -92ppm) is attributed to extensive hydrolysis and silanol condensation or cross-linkage resulting in higher surface coverage and efficiency (5.24µmol/m²). The relative low intensity of Q³ and absent or significant reduction of Q² and T¹ are indicative of a lower degree of residual silanols activity following silanisation in sc-CO₂.

Fig. 4. 29 Si CP/MAS NMR spectrum of APS prepared from DMAPTMS using sc-CO₂ as reaction medium.

The ¹³C CP/MAS NMR spectrum revealed all peaks associated with the carbon atoms of the DMAPTMS ligands with the exception of the methoxy carbon atoms (Fig. 5). The peak at 13ppm correspond to the carbon atom (C-1) directly attached to silica, while peaks at 23 ppm and 65ppm correspond to the second (C-2) and third (C-3) methyl carbons of the propyl chain respectively. The peak at 36ppm is attributed to the carbon atoms (C-4) directly attached to the nitrogen atom of DMAPTMS ligand. The absent of a peak associated with carbon atoms of the methoxy groups (-OCH₃) is further evidence of extensive hydrolysis and silanols condensation or cross-linkage using sc-CO₂ as a reaction solvent coupled with post-curing at 120°C and consistent with cited results in literature[39].

Fig. 5. 13 C CP/MAS NMR spectrum of APS prepared from DMAPTMS using sc-CO₂ as reaction medium.

4. Conclusions

Supercritical carbon dioxide (sc-CO₂) has been demonstrated as a competitive alternative medium for the synthesis of aminopropyl bonded silica (APS) compared to conventional organic solvents (e.g. toluene) based methods. Using sc-CO₂ conditions of 100°C, 414 bar and 3 h, surface coverages and efficiencies of APS prepared with APTES (5.26µmol/m², 65.75%) and DMAPTMS (4.58µmol/m², 57.25%) are higher but comparable to conventional organic solvents based methods with APTES (4.71µmol/m², 58.88%) and DMAPTMS (4.38µmol/m², 54.75%) at a temperature of 110°C in 24 h. It is expected that the effect on the chromatographic performance of higher surface ligand density obtained with the sc-CO₂ protocol is a decrease in secondary interactions particularly of basic analytes due to lower degree of residual silanol activity.

Zeta potential measurements shows a change in electrostatic charges of silanol groups from negative values for bare Exsil-pure silica to positive for bonded APS due to immobilization of amino groups (- NH_3^+) onto the surface of silica. Moreover, zeta potentials become more positive as carbon loading increases and the values are higher in methanol than in acetonitrile probably due to differences in dipole moment and dielectric constant.

²⁹Si-CP/MAS NMR of APS prepared from DMAPTMS using sc-CO₂ as a reaction medium revealed the present of bound organic moiety on the surface of silica confirming successful functionalisation. The ¹²C-CP/MAS NMR spectrum shows the propyl carbons of used ligand couple with absent of the methoxy groups (-OCH₃) indicating extensive hydrolysis and silanols condensation, further confirming effective sc-CO₂ functionalisation.

Acknowledgements

The authors wish to acknowledge financial support from Science Foundation Ireland (SFI) for the Irish Separation Science Cluster (ISSC) http://www.separationscience.ie/ under their Strategic Research Cluster (SRC) programme (grant 08/SRC/B1412). Acknowledgement also goes to the generous collaboration of Emeritus Professor Albert and Miss Helen Yeman at the Universität Tubingen, Institüt fur Organische Chemie, D-72076 Tubingen, Germany, in particular for assistance with acquisition of ²⁹Si and ¹³C CP/MAS NMR spectra.

References;1;

- [1]K.K. Unger,;1; Porous silica-Its properties and uses as support in column liquid chromatography, Elsevier, Amsterdam, 1979.
- [2]K. Albert,;1; NMR investigation of stationary phases. J. Sep. Sci. 26 (2003) 215-224.
- [3]S. Ray, M. Takafuji, and H. Ihara, 1; Chromatographic evaluation of a newly designed peptide-silica stationary phases in reverse phase liquid chromatography and hydrophilic interaction liquid chromatograpy: Mixed mode behavior. J. Chromatogr. A 1266 (2012) 43-52.
- [4]S. Bocian, A. Nowaczyk, and B. Buszewski, 1; New alkyl-phosphate bonded stationary phases for liquid chromatographic separation of biologically active compounds. Anal Bioanal Chem 404 (2012) 731-740.
- [5]A.A. Muxel, A. Neves, M.A. Camargo, A.J. Bortoluzzi, B. Szpoganicz, E.E. Castellano, Nathalia, T. Bortolotto, and Hernan,;1; New La(III) complex immobilized on 3-aminopropyl-functionalized silica as an efficient and resuable catalyst for hydrolysis of phosphate ester bonds. Inorg. Chem. 53 (2014) 2943-2952.
- [6]S.J. Miller, 1; In search of peptide-based catalysts for asymmetric organic synthesis. Acc. Chem. Res. 37 (2004) 601-610.
- [7]H. Brooks, B. Lebieu, and E. Vives,;1; Tat peptide-mediated cellular delivery:back to basic. Adv. Drug Deliv. Rev. 57 (2005) 559-577.
- [8]A. Erdem, T. Shahwan, A. Cagir, and A.E. Eroglu,;1; Synthesis of amiopropyl triethoxysilanefunctionalized silica and its application in speciation studies of vanadium (IV) and vanadium. Chem. Eng. J. 174 (2011) 76-85.
- [9]M.C. McAlpine, H.D. Agnew, R.D. Rohde, M. Blanco, H. Ahmed, A.D. Stuparu, W.A. Goddard-III, and J.R. Heath,;1; Peptide-nanowire hybrid materials for selective sensing of small molecules. J. Am. Chem. Soc. 130 (2008) 9583-9589.
- [10]S.C. Feifel, and F. Lisdat,;1; Silica nanoparticles for layer-by-layer assembley of fully electro-active cytochrome c multilayers. J. Nanobiotechnol. 9 (2011) 47-59.
- [11]E. Gazit,;1; Self-assembled peptide nanostructures: the design of molecular building bolcks and their technological utilization. Chem. Soc. Rev. 36 (2007) 1263-1269.
- [12]K. Albert, R. Brindle, J. Schmid, B. Buszewski, and E. Bayer,;1; CP/MAS NMR investigations of silica gel surfaces modified with aminopropylsilane. Chromatographia 38 (1994) 283-290.
- [13]L.D. White, and C.P. Tripp, 1; Reaction of (3-aminopropyl)dimethylethoxysilane with amine catalysts on silica surfaces. J. Colloid Interface Sci. 232 (2000) 400-407.
- [14]M.-Y. Tsai, C.-Y. Lin, C.-H. Huang, J.-A. Gu, S.-T. Huang, J. Yu, and H. Chen, 1; Vapour-based synthesis of maleimide-functionalized coating for biointerface engineering. Chem. Commun. 48 (2012) 10969-10971.
- [15]S. Jiang, M.J. Schultz, Q. Chen, J.S. Moore, and S. Granick,;1; Solvent-free synthesis of janus colloidal particles. Langmuir 24 (2008) 10073-10077.
- [16]B.A. Ashu-Arrah, J.D. Glennon, and K. Albert, 1; Preparation and characterisation of bonded silica hydride intermediate from triethoxysilane and dimethylmethoxysilane using supercritical carbon dioxide and dioxane as a reaction medium. J. Chromatogr. A 1236 (2012) 42-50.

- [17]B.A. Ashu-Arrah, J.D. Glennon, and K. Albert,;1; Synthesis and characterisation of bonded mercaptopropyl silica intermediate stationary phases prepared using multifunctional alkoxysilanes in supercritical carbon dioxide as reaction solvent. J. Chromatogr. A 1222 (2012) 38-45.
- [18]B.A. Ashu-Arrah, J.D. Glennon, and K. Albert, 1; Synthesis, characterisation and chromatographic evaluation of pentafluorophenyl and phenyl bonded silica phases prepared using supercritical carbon dioxide as a reaction solvent. J.Chromatogr. A 1273 (2013) 34-43.
- [19]B.A. Ashu-Arrah, J.D. Glennon, and K. Albert, 1; Spectroscopic and chromatographic characterisation of a pentafluorophenylpropyl silica phase end-capped in supercritical carbon dioxide as a reaction solvent. J. Chromatogr. A 1298 (2013) 86-94.
- [20]N.M. Scully, B.A. Ashu-Arrah, A.P. Nagle, J.O. Omamogho, G.P. O'Sullivan, V. Friebolin, B. Dietrich, K. Albert, and J.D. Glennon,;1; Silica hydride intermediate for octadecylsilica and phenyl bonded phase preparation via heterogeneous hydrosilation in supercritical carbon dioxide J. Chromatogr. A 1218 (2011) 1974-1982.
- [21]G.P. O'Sullivan, N.M. Scully, and J.D. Glennon,;1; Polar-embedded and polar-endcapped stationary phases for LC. Anal. Letts. 43 (2010) 1609-1629.
- [22]G.P. O'Sullivan, N.M. Scully, J.-M. Prat, J.D. Glennon, B. Dietrich, V. Friebolin, and K. Albert,;1; Synthesis, characterisation and chromatographic evaluation of polyether dendrimer stationary phases. Anal. Bioanal. Chem. 394 (2009) 1261-1272.
- [23]C. Aymonier, A. Loppinet-Serani, H. Reverón, Y. Garrabos, and F. Cansell,;1; J. Supercrit. Fluids 38 (2006) 242-251.
- [24]M.M. Robson, R. Dmoch, I. Bromilow, K.D. Bartle, and P. Myers,;1; Preparation and evaluation of supercritical fluid bonded liquid chromatography stationary phase. High pressure chemical engineering 62 (1999) 43-46.
- [25]J.J. Pesek, M.T. Matyska, E.J. Williamsen, M. Evanchi, V. Hazari, K. Konjuh, S. Takhar, and R. Tranchina,;1; Synthesis and characterization of alkyl bonded phases from a silica hydride via hydrosilation with free radical initiation. J. Chromatogr. A 786 (1997) 219-228.
- [26]C. Cao, A.Y. Fadeev, and T.J. McCarthy,;1; Reactions of organosilane with silica surfaces in carbon dioxide. Langmuir 17 (2001) 757-761.
- [27]T. Yarita, T. Ihara, Y. Horimoto, and A. Nomura,;1; Endcapping of octadecylsilyl-silica gel using supercritical fluid as a reaction medium. Anal. Sci. 15 (1999) 337-380.
- [28]B. McCool, and C.P. Tripp,;1; Inaccessible hydroxyl groups on silica are accesible in supercritical CO₂. J. Phys. Chem. B 109 (2005) 8914-8919.
- [29]C.P. Tripp, and J.R. Combes, 1; Chemical modification of metal oxide surfaces in supercritical CO₂: The interaction of supercritical CO₂ with the adsorbed water layer and the surface hydroxyl groups of a silica surface. Langmuir 14 (1998) 7348-7352.
- [30]J.R. Combes, 1; L.D. white, and C.P. Tripp, Chemical modification of metal oxide surfaces in supercritical CO₂: Insitu infrared studies of the adsorption and reaction of organosilanes on silica. Langmuir 15 (1999) 7870-7875.

- [31]W. Gu, and C.P. Tripp,;1; The reaction of silanes with TiO₂ and Al₂O₃ using supercritical CO₂ (sc-CO₂) as a solvent. Langmuir 22 (2006) 5748-5752.
- [32]L.C. Sander, and S.A. Wise,;1; Synthesis and characterization of polymeric C₁₈ stationary phases for liquid chromatography. Anal. Chem. 56 (1984) 504-510.
- [33]E.A. Smith, and W. Chen, 1; How to prevent loss of surface functionality derived from aminosilanes. langmuir 24(21) (2008) 12405-12409.
- [34]G.E.;1; Berendsen, and L. de-Galan, Preparation and chromatographic properties of some chemically bonded phases for reversed-phase liquid chromatography. J. Liq. Chromatogr. 1 (1978) 561-586.
- [35]G.E. Berendsen, K.A.;1; Pikaart, and L. de-Galan, Preparation of various bonded phases for HPLC using monochlorosilane. J. Liq. Chromatogr. 3 (1980) 1437-1464.
- [36]J.E. Sandoval,;1; Equation for calculating surface coverage from end-capping of chromatographic bonded phases. J. Chromatogr. A 825 (1999) 375-381.
- [37]B. Buszewski, M. Jezierska, M. Welniak, and R. Kaliszan,;1; Cholesteryl-silica stationary phase for liquid chromatography: comparative study of retention bahaviour and selectivity. J. Chromatogr. A 845 (1999) 433-445.
- [38]B. Buszewski, S. Bocian, and E. Dziubakiewicz,;1; Zeta potential determination as a new way of stationary phases characterization for liquid chromatography. J. Sep. Sci. 33 (2010) 1529-1537.
- [39]Z. Lunan, J.A. Fournier, J. Wooten, and D.E. Miser,;1; Preparation and characterization of (3aminopropyl)triethoxysilane-modified mesoporous SBA-15 silica molecular seives. Microporous and Mesoporous Materials 83 (2005) 150-158.

Figure;1; Caption

Α 101 99 97 95 Weight loss (%) TAG weight loss = 7% 93 _,%C = 7.33 APS prepared in toluene 91 89 TGA weight loss = 12% 87 - %C = 8.03 APS prepared in sc-CO2 85 395 454 515 576 638 699 30 150 211 273 334 760 819 880 89 Temperature (°C)

Fig. 1A. TGA overlay with varying loading of aminopropyl groups of bonded APS intermediate phase prepared with 3-APTES using sc-CO₂ and toluene as reaction medium.



Figr-1List of figures

Fig. 1B. TGA/DTA of bonded APS intermediate phase prepared with DMAPTMS in toluene showing 3 distinct decomposition steps.



Fig. 2. SEM micrographs of bare silica and APS phase generated from APTES using sc-CO₂ and toluene as reaction medium.



Fig. 3. DRIFT spectra of APS (APTES) generated in sc-CO₂ at conditions of 100°C/414bar/3 h.



Fig. 4. 29 Si CP/MAS NMR spectrum of APS prepared from DMAPTMS using sc-CO₂ as reaction medium.



Fig. 5. 13 C CP/MAS NMR spectrum of APS prepared from DMAPTMS using sc-CO₂ as reaction medium.

List of tables

Table 1. Elemental analysis values of APS intermediate prepared from 3-APTES and N, N-DMAPTMS) using sc-CO₂ ($100^{\circ}C/414bar/3 h$) and toluene ($110^{\circ}C/24 h$) as reaction medium.

Property of silica used	Silanisation process	%C, %H, %N, C/N
Exsil-Pure silica, 3 µm,	APTES in sc-CO ₂ , 3 h /100°C/ 414 bar	8.03, 1.76, 2.36, 3.40
120 Å, 223 m ² /g		
Exsil-Pure silica, 3 µm,	APTES in toluene, 24 h /110°C	7.33, 1.64, 2.51, 2.92
120 Å, 223 m ² /g		
Exsil-Pure silica, 3 µm,	DMAPTMS in sc-CO ₂ , 3h/100°C/414 bar	5.12, 1.17, 1.12, 4.57
120 Å, 223 m ² /g		
Exsil-Pure silica, 3 µm,	DMAPTMS in toluene, 24 h/110°C	4.93, 1.81, 1.01. 3.92
120 Å, 223 m ² /g		
Porous silica of particle	APTES in toluene, 24 h /110°C ^a	6.16, 1.85, 2.17, -
diameter 0.2-0.5 nm		
YMC silica (SIL-120-S5),	APTMS in toluene, 24 h ^b	6.54, 2.09, 2.25, 2.90
5 μm		
Kromasil 100 Å, 5µm, 313	APTMS in toluene, $12 \text{ h} / 120^{\circ} \text{C}^{\circ}$	2.83, 1.31, 1.25, -
m^2/g		
^a Reference: Erdem <i>et al</i> .[8]		

^b Reference: Ray *et al.*[3]

^c Reference: [4]

-, Value not available

Table 2. Surface coverages	and TGA mass l	loss (%w/w) of APS	prepared with	APTES and
DMAPTMS using sc-CO ₂ a	nd toluene as react	tion medium.		

Properties of silica	Silanisation process	%C	TGA mass loss	$\alpha (\mu mol/m^2)$
used				а
Exsil-Pure silica,	APTES in sc-CO ₂ ,	8.03	12% from 220 -	5.26
3µm,	3 h/100°C/414 bar		880°C	
120Å, 223m²/g				
Exsil-Pure silica,	APTES in toluene,	7.33	7% from 220 -	4.71
3μm,	24 h/110°C		880°C	
120Å, 223m²/g				
Exsil-Pure silica,	DMAPTMS in sc-CO ₂ ,	5.12	-	4.58
3µm,	3 h/100°C/414 bar			
120Å, 223m²/g				
Exsil-Pure silica,	DMAPTMS in toluene,	4.93	10% from 220 -	4.38
3μm,	24 h/ 110°C		880°C	
120Å, 223m²/g				
Kromasil 100Å, 5µm,	APTES in toluene, 12 h,	4.47	-	4.67
310 m ² /g	100°C ^b			
Kromasil 100Å, 5µm,	APTMS in toluene, 12 h,	2.83	-	2.8
313 m ² /g	120°C ^c			
YMC silica (SIL-120-	APTMS in toluene, 24 h	6.54	8.07% from 200	6.74
S5), 5µm	d		-800°C	
			$10^{6} \times \% C$	

^a Surface coverage calculated based on de Galan equation: $\alpha(\mu mol/m^{-2}) = \frac{10^{\circ} \times \%C}{S_{BET}(100Cn_c - \%CM_r)}$

^b Reference: [36] ^c Reference: [4] ^d Reference: [3] -, Data not available

Table 3 . Zeta Potential (mV) for bare silica and functionalized APS prepared from APTES						
Phase	Bar	e silica	SC-	-APS	org-A	APS
Dispersant	Methanol	Acetonitrile	Methanol	Acetonitrile	Methanol	Acetonitrile
Average ξ	-24.3	-34.9	+45.8	+28.8	+33.0	+24.7

Table 4. Physicochemical properties of methanol and acetonitrile used in zeta potential
 analysis at 25°C^a

Properties	Symbol	Methanol	Acetonitrile
Refractive index (RI)	n	1.326	1.345
Viscosity (cP)	ç	0.5476	0.400
Dielectric constant	å _r	33.0	37.5
Dipole moment (D) ^b	μ	1.854	3.184

^a Data from DTS (nano) software ver.510 ^b Reference:[38]