CORA Cork Open Research Archive
Cartlann Taighde Oscailte Chorcaí

Title	Absence of evidence ≠ evidence of absence: statistical analysis of inclusions in multiferroic thin films
Authors	Schmidt, Michael;Amann, Andreas;Keeney, Lynette;Pemble, Martyn E.;Holmes, Justin D.;Petkov, Nikolay;Whatmore, Roger W.
Publication date	2014-07-16
Original Citation	SCHMIDT, M., AMANN, A., KEENEY, L., PEMBLE, M. E., HOLMES, J. D., PETKOV, N. & WHATMORE, R. W. 2014. Absence of Evidence ≠ Evidence of Absence: Statistical Analysis of Inclusions in Multiferroic Thin Films. Scientific Reports, 4, 5712. http://dx.doi.org/10.1038/srep05712
Type of publication	Article (peer-reviewed)
Link to publisher's version	10.1038/srep05712
Rights	© Schmidt et al, 2014; licensee Nature Publishing Group, 2015. This work is licensed under a Creative Commons Attribution-NonCommercialNoDerivs 4.0 International License. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in the credit line; if the material is not included under the Creative Commons license, users will need to obtain permission from the license holder in order to reproduce the material. To view a copy of this license, visit http://creativecommons.org/licenses/by-nc-nd/4.0/ - http://creativecommons.org/licenses/by-nc-nd/4.0/
Download date	2026-11-04 06:46:25
Item downloaded from	https://hdl.handle.net/10468/2405



University College Cork, Ireland
Coláiste na hOllscoile Corcaigh

Supporting information for manuscript titled 'Absence of Evidence ≠ Evidence of Absence: Statistical Analysis of Inclusions in Multiferroic Thin Films'

Michael Schmidt[1,2*], Andreas Amann[1,3], Lynette Keeney[1], Martyn E. Pemble[1,2], Justin D. Holmes[1,2,4], Nikolay Petkov[1] and Roger W. Whatmore[1,2,5]

1. Tyndall National Institute, University College Cork, 'Lee Maltings', Dyke Parade, Cork, Ireland.

2. Department of Chemistry, University College Cork, Cork, Ireland

3. School of Mathematical Sciences, University College Cork, Ireland.

4. Centre for Research on Adaptive Nanostructures and Nanodevices, Trinity College Dublin, Dublin 2, Ireland

5. Department of Materials, Royal School of Mines, Imperial College London, South Kensington Campus, London SW7 2AZ, UK

A. Site specific cross section preparation




Figure S1. Site specific TEM cross section sample preparation on the B6TFMO. a) One ‘small bright spot’ and one ‘large pale area‘ were chosen, b) marked with carbon pillars, c) protected with platinum. d) Lamella prepared, e) lifted out, before attached to TEM half grid and f) analysed with STEM.

B. Representative TEM images




Figure S2. Representative TEM images of B6TFMO from the 30µm long lamella. The single crystalline grains are tightly packed without any appearing inclusions of different phases. The scale bar is 20 nm. f) Here a BTF7C3O sample is depicted for comparison to illustrate the presence of inclusions (bright grain at the middle right hand side of the image, scale bar 100 nm). [1]

1 Keeney, L. *et al.* Room temperature ferroelectric and magnetic investigations and detailed phase analysis of Aurivillius phase $Bi_5Ti_3Fe_{0.7}Co_{0.3}O_{15}$ thin films. *JAP* **112**, 052010 (2012).