

Title	Electronic and optical properties of SixGe1-x-ySny alloys lattice-matched to Ge
Authors	Pearce, Phoebe M.;Broderick, Christopher A.;Nielsen, Michael P.;Johnson, Andrew D.;Ekins-Daukes, Nicholas J.
Publication date	2022-01-18
Original Citation	Pearce, P. M., Broderick, C. A., Nielsen, M. P., Johnson, A. D. and Ekins-Daukes, N. J. (2022) 'Electronic and optical properties of SixGe1-x-ySny alloys lattice-matched to Ge', Physical Review Materials, 6(1), 015402 (15pp). doi: 10.1103/PhysRevMaterials.6.015402
Type of publication	Article (peer-reviewed)
Link to publisher's version	10.1103/PhysRevMaterials.6.015402
Rights	© 2022, American Physical Society. All rights reserved.
Download date	2026-10-12 16:15:29
Item downloaded from	https://hdl.handle.net/10468/13084

Electronic and optical properties of $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys lattice-matched to Ge

Phoebe M. Pearce^{1,*}, Christopher A. Broderick^{2,3,†}, Michael P. Nielsen⁴, Andrew D. Johnson⁵, and Nicholas J. Ekins-Daukes^{1,4}

¹*Department of Physics, Imperial College London, South Kensington, London SW7 2AZ, United Kingdom*

²*Tyndall National Institute, University College Cork, Lee Maltings, Dyke Parade, Cork T12 R5CP, Ireland*

³*Department of Physics, University College Cork, Cork T12 YN60, Ireland*

⁴*School of Photovoltaic and Renewable Engineering, University of New South Wales, Sydney, New South Wales 2052, Australia*

⁵*IQE plc., Pascal Close, St. Mellons, Cardiff CF3 0LW, United Kingdom*



(Received 21 September 2021; accepted 21 December 2021; published 18 January 2022)

We present a combined experimental and theoretical analysis of the evolution of the near-band-gap electronic and optical properties of $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys lattice-matched to Ge and GaAs substrates. We perform photoreflectance (PR) and photoluminescence (PL) measurements on $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ epitaxial layers grown via chemical vapor deposition for Si (Sn) compositions up to $x = 9.6\%$ ($y = 2.5\%$). Our measurements indicate the presence of an indirect fundamental band gap, with PL observed $\approx 200\text{--}250$ meV lower in energy than the direct E_0 transition identified by PR measurements. The measured PL is Ge-like, suggesting that the alloy conduction band (CB) edge is primarily derived from the Ge L -point CB minimum. Interpretation of the PR and PL measurements is supported by atomistic electronic structure calculations. Effective alloy band structures calculated via density functional theory confirm the presence of an indirect fundamental band gap, and reveal the origin of the observed inhomogeneous broadening of the measured optical spectra as being alloy-induced band hybridization occurring close in energy to the CB edge. To analyze the evolution of the band gap, semiempirical tight-binding (TB) calculations are employed to enable calculations for large supercell sizes. TB calculations reveal that the alloy CB edge is hybridized in nature, consisting at low Si and Sn compositions of an admixture of Ge L -, Γ -, and X -point CB edge states, and confirm that the alloy CB edge retains primarily Ge L -point CB edge character. Our experimental measurements and theoretical calculations confirm a direct transition energy close to 1 eV in magnitude for Si and Sn compositions $x = 6.8\%\text{--}9.6\%$ and $y = 1.6\%\text{--}2.2\%$.

DOI: [10.1103/PhysRevMaterials.6.015402](https://doi.org/10.1103/PhysRevMaterials.6.015402)

I. INTRODUCTION

$\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys have attracted increasing research interest due to their potential for a variety of device applications [1,2], including diode lasers [3,4], light-emitting diodes [5,6], photovoltaics [5,7–9], photodiodes [10], and tunneling field-effect transistors [11,12]. For applications in multijunction solar cells, a material lattice-matched to Ge or GaAs having an absorption edge close to 1 eV is especially useful as it can be incorporated into well-developed device architectures [13]. The composition range for $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys suitable for application as a 1-eV junction in a multijunction solar cell is Ge rich ($\gtrsim 85\%$), with a Si to Sn composition ratio $x : y \approx 3.7 : 1$ required to achieve lattice matching. Beginning from Ge, incorporation of Si increases the energy of both the fundamental indirect band gap ($L_{6c}\text{--}\Gamma_{8v}$; 0.67 eV in Ge) and the lowest-energy direct transition ($\Gamma_{7c}\text{--}\Gamma_{8v}$; 0.80 eV in Ge), while simultaneously reducing the lattice constant due to the lower covalent radius of Si compared to Ge. Conversely, incorporation of Sn acts to reduce the magnitude of the indirect and direct band gaps, while simultaneously increasing

the lattice constant [8,14,15]. By balancing the relative composition of Si and Sn in the alloy, it is therefore possible to engineer a material having higher fundamental band gap and absorption edge energies than Ge, but the same lattice constant [8,14,16,17].

Here, we present a combined experimental and theoretical analysis of the evolution of the electronic and optical properties of $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys lattice-matched to Ge and GaAs. Experimentally, we describe sample growth via low-pressure chemical vapor deposition (CVD), while the direct interband optical transitions are probed using photoreflectance (PR) measurements. Photoluminescence (PL) measurements are employed to investigate the fundamental indirect band gap. Theoretically, we analyze the electronic structure evolution with alloy composition, first using first-principles calculations based on density functional theory (DFT), which we apply to compute effective (unfolded) band structures for alloy special quasirandom structures (SQSs) [18,19]. These calculations identify strong alloy-induced band hybridization close in energy to the conduction band (CB) edge in energy, which we then probe via large-supercell semiempirical calculations based on a parametrized valence force field (VFF) potential and tight-binding (TB) Hamiltonian [20].

We focus on the evolution of the near-band electronic and optical properties, quantifying the nature of the indirect and direct interband transitions critical to optoelectronic

*Present address: School of Photovoltaic and Renewable Energy Engineering, University of New South Wales, Sydney, New South Wales 2052, Australia; p.pearce@unsw.edu.au

†c.broderick@umail.ucc.ie




FIG. 1. Schematic illustration of the structure of the epitaxial $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples investigated in this work. (a) Sample set A: grown on GaAs substrates, with a thin Ge seed layer. (b) Sample set B: grown on Ge substrates, with a thick lattice-matched $\text{In}_{0.012}\text{Ga}_{0.988}\text{As}$ buffer layer. Layer thicknesses indicated in (a) and (b) are the nominal thicknesses targeted during CVD growth.

and photovoltaic device applications. Our measurements and calculations demonstrate that the fundamental band gap in lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys suitable for solar cell applications remains indirect, but is larger than the fundamental $L_{6c}-\Gamma_{8v}$ band gap of Ge. The lowest-energy direct transition, which dominates the absorption edge of the material, is shown to be readily tunable to the $\approx 1\text{-eV}$ values required for optimized three- and four-junction solar cells. In a solar cell, the maximum achievable subcell current is limited by the fundamental band gap, while the direct absorption edge energy is important from the perspective of current matching. In addition to providing insight into the complexities of the electronic and optical properties of this emerging material system, our results suggest the potential to achieve higher current and improved current matching in multijunction solar cells having a $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ 1-eV junction.

II. EXPERIMENTAL METHODS

A. Sample growth and characterization

$\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples were grown via low-pressure CVD using an ASM Epsilon 2000 reactor, with germane (GeH_4), disilane (Si_2H_6), and tin chloride (SnCl_4) precursors, and using H_2 as the carrier gas. Two sets of samples were grown across the composition range of interest. The first, set A, was grown on GaAs substrates with a thin ($\approx 60\text{-nm}$) Ge seed layer. The second, set B, was grown on Ge substrates which were overgrown via metal-organic vapor phase epitaxy with a $\approx 500\text{-nm}$ buffer layer of $\text{In}_{0.01}\text{Ga}_{0.99}\text{As}$ lattice-matched to Ge. The layer structures of sample sets A and B are depicted schematically in Figs. 1(a) and 1(b), respectively. Samples were grown for a range of Si and Sn compositions x and y , aiming in all cases for a composition ratio $x : y \approx 3.7 : 1$ to achieve lattice matching to Ge, with this composition ratio derived under the assumption that the alloy lattice constant $a(x, y)$ obeys Vegard's law [21], and using room-temperature Si, Ge, and $\alpha\text{-Sn}$ lattice constants [22]. Both sets of samples include three different combinations of Si and Sn composition, and for sample set B two different structures having thin ($\sim 0.4\text{ }\mu\text{m}$) and thick ($\sim 2\text{ }\mu\text{m}$) $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ layers with

TABLE I. Details of the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples investigated. Sample set A was grown on GaAs substrates, using a Ge buffer layer [cf. Fig. 1(a)]. Sample set B was grown on Ge substrates, using a $\text{In}_{0.012}\text{Ga}_{0.988}\text{As}$ buffer layer [cf. Fig. 1(b)]. Listed $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ layer thicknesses d were obtained from fits to measured PR spectra. Two sets of B samples were grown: “thin” $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ layers having thickness $\sim 0.4\text{ }\mu\text{m}$, and “thick” layers having thickness $\sim 2\text{ }\mu\text{m}$. Listed Si and Sn compositions x and y are the mean value and standard deviation obtained from 10 SEM-EDX measurements performed on each sample. Composition measurements for the set B samples were performed only for the thicker samples, with the thinner samples grown under the same conditions and assumed to have the same composition.

Sample	d (nm)	Si, x (%)	Sn, y (%)	Ratio, $x : y$
A1	1811	4.6 ± 0.2	0.9 ± 0.1	5.11 : 1
A2	1746	6.8 ± 0.4	1.6 ± 0.1	4.25 : 1
A3	1828	9.6 ± 0.4	2.2 ± 0.1	4.36 : 1
B1 (thin)	332			
B2 (thin)	362			
B3 (thin)	353			
B1 (thick)	2073	2.6 ± 0.3	0.8 ± 0.2	3.25 : 1
B2 (thick)	2017	5.9 ± 0.2	1.5 ± 0.1	3.93 : 1
B3 (thick)	2036	8.4 ± 0.2	2.5 ± 0.1	3.36 : 1

nominally equal alloy compositions were grown, yielding a total of nine samples with six different alloy compositions. The resulting sample structures, Si and Sn compositions, and sample layer thicknesses (obtained via fits to measured PR data) are summarized in Table I. The Si and Sn compositions of the samples were measured using scanning electron microscopy with energy-dispersive x-ray (SEM-EDX) spectroscopy. These composition measurements, in addition to x-ray diffraction and spectroscopic ellipsometry measurements for these samples, are discussed in Ref. [23]. The sample layer thicknesses reported in Ref. [23], obtained via fitting to spectroscopic ellipsometry data, are in good agreement with the values obtained here via fitting to PR data (cf. Sec. II B).

B. Photoreflectance spectroscopy

The energy E_0 associated with the direct (optical, $\Delta \mathbf{k} = 0$) transition between the zone-center Γ_{8v} valence band (VB) and Γ_{7c} CB edges, and the energy $E_0 + \Delta_0$ associated with the direct transition between the zone-center Γ_{7c} CB edge and the Γ_{7v} spin-split-off (SO) VB, were studied using PR. PR is a contactless modulation spectroscopy technique that allows measurement of transition energies associated with direct interband transitions in semiconductors via modulation of the internal electric field as carriers are photogenerated with a laser pump beam. The $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples were doped (p type, $n_a \approx 5 \times 10^{15}\text{ cm}^{-3}$). This generates an internal electric field due to pinning of the Fermi energy at the sample surface, which will have an excess of majority carriers (holes). When carriers are generated at the sample surface by the pump beam, this internal field causes the electrons and holes to be separated with the minority carriers (electrons) swept towards the surface. This carrier separation acts to screen

the internal electric field, and thus the field is modulated by the laser [24]. Sample reflectivity is measured via a probe beam, both with and without the effect of the pump beam, allowing the change in reflectivity ΔR due to the pump beam to be determined. PR is therefore a differential measurement technique, making it highly sensitive to critical points in the material band structure. In order to eliminate the effect of PL due to the laser pump beam from the PR measurements, and measure R and ΔR simultaneously, both the probe and pump beams were chopped at different frequencies in a double demodulation method [25]. As such, the ΔR signal was measured at the sum of the frequencies of the probe and pump beams, while the R signal was directly measured at the probe chopping frequency. ΔR and R can thus be measured using a single detector and extracted via lock-in detection, which in our measurements was performed using a Zurich Instruments HF2 lock-in amplifier, with signal gain accomplished using a Zurich Instruments HF2TA current amplifier. The pump beam used is a GEM 532 nm (2.33 eV) continuous-wave laser incident at an angle of $\approx 5^\circ$ to the sample surface with an intensity of 164 W cm^{-2} . The probe beam was generated using a Bentham IL1 100 W halogen lamp coupled to a Bentham TMC300 monochromator. The spectral range is limited by the laser wavelength (532 nm) at short wavelength (since there will be significant noise around the laser wavelength), and by the detector response at long wavelength (1700 nm). The probe beam was focused on the sample at an angle of 45° , and the reflected beam was measured using a Thorlabs DET10N2 biased InGaAs detector with a detection range of 500–1700 nm.

Critical points in the measured PR spectra were analyzed by fitting the experimental data to an expression formed of a sum of third-derivative functional forms [26]

$$\frac{\Delta R}{R} = \text{Re} \left\{ \frac{A_0 e^{i\Phi_0}}{(E - E_0 + i\Gamma_0)^{5/2}} + \frac{A_{\text{ex}} e^{i\Phi_{\text{ex}}}}{(E - E_{\text{ex}} + i\Gamma_{\text{ex}})^2} + \frac{A_{\Delta_0} e^{i\Phi_{\Delta_0}}}{[E - (E_0 + \Delta_0) + i\Gamma_{\Delta_0}]^{5/2}} \right\}, \quad (1)$$

where the energetic (lifetime) broadening Γ , amplitude A , and phase Φ in each term are assumed to be independent of photon energy E .

The first and third terms in Eq. (1) represent the third derivative with respect to energy of the expected form of the dielectric function around a three-dimensional M_0 -type critical point [27,28], and correspond, respectively, to contributions to $\frac{\Delta R}{R}$ from CB-VB (Γ_{7c} - Γ_{8v}) and CB-SO (Γ_{7c} - Γ_{7v}) transitions having respective energies E_0 and $E_0 + \Delta_0$. The second term represents the excitonic contribution to the third derivative of the dielectric function close in energy to the E_0 critical point, at energy E_{ex} . The measured PR spectrum for a Ge (substrate) reference sample shows a symmetrical peak shape close in energy to the direct Γ_{7c} - Γ_{8v} transition [27] having three sharp extrema. It is not possible to achieve this peak shape by fitting only a single critical point feature at the E_0 feature, hence, the inclusion of the excitonic contribution. To analyze the PR data of the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples, it was necessary to account for the impact of the clear thin-film interference effects observed in the PR data. The PR data for the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples with layer thickness $\approx 2 \mu\text{m}$ showed

multiple oscillation fringes about, and below, the expected E_0 energy, while the data for the thinner set B samples show more clearly defined E_0 and $E_0 + \Delta_0$ features which blueshift with increasing Si and Sn composition.

Although fringes due to Franz-Keldysh oscillations can occur in PR measurements [29], these occur at energies above the critical point, while the oscillations observed here are below the E_0 energies expected from theory and observed in spectroscopic ellipsometry analysis of the same samples [23]. Comparing the data for the thicker and thinner set B samples also shows that these oscillations are primarily visible at energies below and close to the E_0 critical point feature. The width of the fringes corresponds to the width expected due to thin-film oscillations for light incident at 45° (the angle of incidence of the probe beam with respect to the sample surface). The measured PR spectra for the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples were thus fitted using a combined critical point and interference fringe model [30], with the exception of the Ge reference sample, which was fitted using Eq. (1) directly. Previous work investigating the appearance of interference fringes in PR spectra [31–33] has attributed the fringes to either modulation of the refractive index of doped materials [31,32] or temperature changes in the sample [33]. Our fitting approach assumes that the fringes are due to the former, and expands upon previous models by self-consistently computing the unmodulated and modulated optical constants from the critical point energies, and feeding these optical constants into a transfer-matrix method simulation [34] to compute the modulated and unmodulated reflectivity and yield the total PR spectrum. Full details of the fitting procedure are described in the Supplemental Material [30].

C. Photoluminescence spectroscopy

PL measurements were performed using excitation from a continuous-wave Spectra-Physics Millennia V Nd:YVO₄ laser with a wavelength of 532 nm (2.33 eV), and an incident power between 100 mW and 3 W (corresponding to incident intensities of 0.12–3.68 kW cm⁻², taking into account the laser spot size). The high photon energy means that most of the incident photons are absorbed within a few hundred nm of the sample surface, which ensures carriers are excited in the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ epitaxial layer rather than the Ge or GaAs substrate (assuming that the absorption in the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ epitaxial layers considered here is Ge-like at high incident photon energies of 2.33 eV, > 99% of the incident laser power will be absorbed in the first 500 nm of material). The resulting PL signal was dispersed through a 0.5-m Princeton Acton SP2500i spectrometer and detected using a liquid-nitrogen-cooled Hamamatsu G7754-01 extended InGaAs detector. The monochromator was scanned across a wavelength range of 1000–2100 nm. The PL signal was processed via standard phase-sensitive detection techniques, using a Stanford SR830 lock-in amplifier. All PL measurements were performed at room temperature ($T = 293 \text{ K}$).

Power-dependent PL measurements were performed for the Ge reference and $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy samples, with the range of incident laser intensities used for each sample chosen depending on its observed luminescence intensity. The Ge substrate was found to have significantly higher PL intensity

than any of the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples, being approximately an order of magnitude higher in terms of both peak and integrated intensity compared to the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ sample displaying the highest PL intensity, sample A1. Due to the observed large spread in luminescence intensities, the PL measurements were not performed at the same incident intensities for all samples, but rather the samples were divided into two groups. The Ge reference sample, as well as the alloy samples A1 and A3, which had the highest intensities of the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples, were measured at intensities between 0.12 and 2.46 kW cm^{-2} . PL measurements for the four remaining samples A2, B1, B2, and B3 were performed at intensities between 1.23 and 3.68 kW cm^{-2} . Due to the high incident laser power, especially for the second set of samples, local sample heating in the illuminated spot may be significant. To analyze this effect we have, at a given incident laser power, (i) calculated the increase in lattice temperature via numerical solution of the heat equation, and (ii) estimated the carrier temperature by fitting a Boltzmann distribution to the high-energy tail of the measured PL spectrum [30]. First, (i) reveals that the maximum local increase in sample lattice temperature, relative to the ambient room temperature $T = 293 \text{ K}$, is expected to be up to $\approx 70 \text{ K}$ ($\approx 100 \text{ K}$) for an incident intensity of 2.46 kW cm^{-2} (3.68 kW cm^{-2}). Second, (ii) produces estimated carrier temperatures that are in close quantitative agreement with our calculated lattice temperatures [30], suggesting the presence of carrier populations in thermal equilibrium with the lattice. To minimize the effects of sample heating on the interpretation of our measured PL spectra, band gaps were obtained solely from fits to our lowest-power measurements.

Both the Ge and $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples show multiple clear peaks in their PL spectra. For Ge the distinct PL peaks can be attributed to indirect (phonon-assisted) radiative recombination pathways [35], with the exception of the highest-energy peak close to $0.78 \text{ eV} \approx E_0$ which is attributed to direct ($\Delta\mathbf{k} = 0$) radiative recombination across the Γ_{7c} - Γ_{8v} transition. To quantify the relative strength of the observed multiple peaks in the measured PL spectra, each spectrum was fitted using a combination of Gaussian and Lorentzian line shapes. The specific line shape used to fit to each peak was chosen to provide the best fit to the measured line shape of that peak. Generally, it was found that most peaks were best described using a Gaussian line shape, with the exception of the highest-energy peak corresponding to emission across the direct transition, which were best described using a Lorentzian line shape. For each PL spectrum the number of distinct peaks to include in the fit was determined via a combination of counting the visible peaks and fitting the data to identify the number of peaks. The fitting parameters employed for each peak were the center (transition) energy, linewidth broadening, and intensity. Full details of the fitting procedure are described in the Supplemental Material [30].

III. THEORETICAL METHODS

A. First principles: Density functional theory

Our alloy supercell DFT calculations for ternary $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys are based closely upon those we

have recently established for binary $\text{Ge}_{1-y}\text{Sn}_y$ alloys, details of which can be found in Ref. [20]. Calculation of structural properties (lattice relaxation) proceeds in the local density approximation (LDA), with subsequent electronic structure calculations performed using the Tran-Blaha modified Becke-Johnson (TB-mBJ) exchange-correlation potential [36]. Our DFT calculations were performed using the projector augmented wave method [37,38], as implemented in the Vienna *ab initio* simulation package (VASP) [39,40]. All calculations explicitly include spin-orbit coupling. Cut-off energies, $\mathbf{k}$ -point grids, choice of pseudopotentials, and convergence criteria for lattice relaxation are as in Ref. [20]. To determine combinations of Si and Sn composition x and y which maintain lattice matching to a Ge substrate, we estimate the alloy lattice constant $a(x, y)$ via linear interpolation (Vegard's law) between the LDA-calculated lattice constants $a = 5.403, 5.647$, and $6.480 \text{ \AA}$ for Si, Ge, and α -Sn, respectively [41]. Setting $a(x, y) = a(\text{Ge})$ we compute a composition ratio $x : y = 3.41 : 1$ for lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$. This composition ratio is unchanged if lattice constants calculated via hybrid functional (HSEsol) DFT are employed [41]. We note that the lattice-matched composition ratio $x : y = 3.41 : 1$ obtained from our zero-temperature DFT calculations differs slightly from the ratio 3.7:1 estimated in Sec. II A using measured lattice constants. We emphasize that the experimental lattice constants cited in Sec. II A were measured at room temperature, and therefore expect that the difference in thermal expansion coefficient between Ge, Si, and α -Sn accounts for the difference in lattice-matched composition ratios. In our DFT (TB) calculations we employ the LDA-calculated composition ratio $x:y = 3.41:1$ for the generation of lattice-matched supercells, for consistency with our LDA-DFT (VFF) relaxation of these structures.

Figure 2 shows the TB-mBJ DFT-calculated bulk band structures of (a) Si, (b) Ge, and (c) α -Sn. Si and Ge are indirect-gap semiconductors, while α -Sn is an inverted-gap semimetal possessing topologically nontrivial band ordering (in which the s -like Γ_{7c} states lie intermediate in energy between the p -like Γ_{8v} and Γ_{7v} states) [42,43]. We note that the increasing X - L - Γ energy ordering of the high-symmetry point CB edge energies in Si is distinct from the L - Γ - X ordering in Ge. This, as well as the known tendency of Sn incorporation to induce Γ - L - X ordering, i.e., a direct fundamental band gap, when incorporated in low concentrations in Ge, suggests that ternary $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys can admit several distinct CB orderings [44]. It is therefore critical to understand the evolution of L -, Γ -, and X -point CB edge states with composition in semiconducting $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$, i.e., at low Sn composition y , in order to develop a quantitative understanding of the alloy electronic structure.

Our previous analysis of $\text{Ge}_{1-y}\text{Sn}_y$ alloys revealed that Sn incorporation drives strong alloy-induced mixing (hybridization) between Ge Γ - and L -point CB edge states [2,20,45]. Alloy supercell calculations reveal that the $\text{Ge}_{1-y}\text{Sn}_y$ alloy CB minimum is formed of an admixture of Ge Γ_{7c} and L_{6c} states, with the nature of the alloy band gap evolving continuously from indirect (predominantly Ge L_{6c} -like) to direct (predominantly Ge Γ_{7c} -like) as the Sn composition y increases [20,46]. Since for photovoltaic applications we are interested




FIG. 2. Band structures of (a) Si, (b) Ge, and (c) α -Sn, calculated via DFT using the TB-mBJ exchange-correlation potential, and including spin-orbit coupling [20]. In each case the zero of energy is chosen to lie at the Γ_{8v} VB edge.

in Ge-rich $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys having $x + y \lesssim 15\%$, i.e., containing $\gtrsim 85\%$ Ge, we expect that alloy band mixing effects in the CB will also play an important role in determining the details of the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy electronic structure. As such, the choice of alloy supercells employed in our DFT calculations must be such that band mixing between Γ -, L -, and X -point states is permitted to occur [20,46]. This is achieved by selecting 128-atom ($4 \times 4 \times 4$ face-centered-cubic) supercells, in which the L and X points of the underlying diamond Brillouin zone fold back to the supercell zone center (at supercell wave vector $\mathbf{K} = 0$). To provide a reliable description of short-range alloy disorder, we employ 128-atom SQSs in our DFT calculations: beginning with a Ge_{128} supercell we substitute a given number of Ge atoms by Sn, determining the Sn composition y and hence the Si composition $x = 3.41y$ required to achieve lattice matching to Ge. The resulting alloy supercell is then relaxed using the LDA exchange-correlation functional, and the electronic structure of the relaxed supercell is computed using the TB-mBJ exchange-correlation potential. The SQSs used in our calculations were generated using the alloy theoretic automated toolkit (ATAT) [47,48], by optimizing the lattice correlation functions up to third-nearest-neighbor distance about a given lattice site with respect to target correlation functions corresponding to a randomly disordered ternary alloy [49].

To analyze the evolution of the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ band gap, we compute the effective band structure [50,51] by unfolding the TB-mBJ-calculated alloy SQS band structure onto a diamond primitive unit-cell Brillouin zone defined by the LDA-relaxed alloy lattice constant $a(x, y) \approx a(\text{Ge})$. This is achieved by calculating the total spectral weight $N(\mathbf{k}, E)$, where $\mathbf{k}$ is the wave vector in the primitive unit-cell Brillouin zone onto which the supercell band structure is being unfolded. $N(\mathbf{k}, E)$ at a given primitive cell wave vector $\mathbf{k}$, in an energy interval of width ΔE centered at energy E , is computed by accumulating the individual supercell eigenstate spectral weights $W_{n\mathbf{K}}$ within that energy interval as [52,53]

$$N(\mathbf{k}, E) = \int_{E-\frac{\Delta E}{2}}^{E+\frac{\Delta E}{2}} \sum_{n,\mathbf{K}} W_{n\mathbf{K}} \delta(E' - E_n(\mathbf{K})) dE', \quad (2)$$

where $W_{n\mathbf{K}} = \langle n\mathbf{K} | \hat{P}(\mathbf{K} \rightarrow \mathbf{k}) | n\mathbf{K} \rangle$ is the spectral weight associated with the unfolding of supercell eigenstate $|n\mathbf{K}\rangle$ from supercell wave vector $\mathbf{K}$ to primitive cell wave vector $\mathbf{k}$, as described by the projection operator $\hat{P}(\mathbf{K} \rightarrow \mathbf{k})$ [50,51]. For our calculations here, we set $\Delta E = 5$ meV. All effective band structure calculations were performed using the BANDUP code [52,53]. We note that the integrand of Eq. (2) is the spectral function $A(\mathbf{k}, E)$ [51,52], so that the total spectral weight $N(\mathbf{k}, E)$ is the integrated spectral function in the energy interval $[E - \frac{\Delta E}{2}, E + \frac{\Delta E}{2}]$.

B. Semiempirical: Valence force field potential and tight-binding Hamiltonian

As described above, only states which fold to the same wave vector $\mathbf{K}$ in the supercell Brillouin zone are capable of hybridizing and, as a consequence, careful choice of supercell lattice vectors is required to interrogate band hybridization in small-supercell DFT calculations. More generally, the ability to analyze alloy-induced hybridization effects in atomistic electronic structure calculations is limited by supercell size. As supercell size increases, more states fold to a given $\mathbf{K}$, approaching the case of real alloy, in which all states that can, by symmetry, hybridize will hybridize, in the limit of ultralarge supercell size [2,54]. Indeed, detailed analyses of electronic structure evolution in conventional [54] and highly mismatched [55,56] III-V alloys, as well as group-IV $\text{Ge}_{1-y}\text{Sn}_y$ [2,20] and dilute carbide $\text{Ge}_{1-y}\text{C}_y$ alloys [57], have demonstrated that obtaining quantitative accuracy in the computed electronic properties requires the use of supercells containing $\gtrsim 10^3$ atoms. While rigorous analysis of band hybridization effects can be undertaken using DFT, the limitation of such calculations to supercell sizes $\sim 10^2$ atoms due to computational expense means that hybridization can only occur between the limited number of states which fold to the same $\mathbf{K}$ point. As such, for alloys in which carrier localization or band hybridization play strong roles, i.e., where the widely employed virtual crystal approximation (VCA) breaks down due to its omission of atomistic effects, small-supercell DFT calculations qualitatively capture but often do not quantitatively predict properties observed in experimental measurements.

To overcome this limitation, we employ computationally less expensive semiempirical TB calculations to enable high-throughput analysis of the electronic structure of large alloy supercells. Examining the band structures of Si, Ge, and α -Sn in Figs. 2(a), 2(b), and 2(c), we expect that the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy CB structure will evolve from having an indirect L -point minimum in Ge, towards having either an indirect Δ -direction minimum (in Si-rich alloys), or an “inverted” direct band gap (in Sn-rich alloys) [44,45,58,59]. As such, to track the evolution of the alloy band gap we are interested primarily in analyzing the evolution of character of alloy states lying close in energy to the CB minimum, and in allowing for hybridization between L -, X -, and Γ -point states. To achieve this we again select supercells in which both L - and X -point states fold back to the supercell zone center $\mathbf{K} = 0$. We therefore perform calculations for 1024-atom ($8 \times 8 \times 8$ face-centered-cubic) $\text{Si}_M\text{Ge}_{1024-M-N}\text{Sn}_N$ supercells, having respective Si and Sn compositions $x = \frac{M}{1024}$ and $y = \frac{N}{1024}$, with the numbers M and N of substitutional Si and Sn atoms chosen to remain as close to lattice-matched to Ge as possible ($M : N \approx 3.41 : 1$). The atomic positions in each alloy supercell are relaxed using a highly accurate (analytically parametrized) VFF potential [20,41], implemented using the general utility lattice program (GULP) [60–62], and the alloy eigenstates at $\mathbf{K} = 0$ are calculated via direct diagonalization of the alloy supercell TB Hamiltonian [20]. We note that our semiempirical (VFF + TB) calculations here are based closely on those established and carefully benchmarked against DFT alloy supercell calculations for $\text{Ge}_{1-y}\text{Sn}_y$, full details of which can be found in Ref. [20].

To investigate the nature and evolution of the alloy CB structure, and to quantify alloy-induced hybridization between Ge host matrix eigenstates, we take selected unperturbed Ge eigenstates $|n^{(0)}\rangle$, having energies $E_n^{(0)}$, and project them onto the complete spectrum of $\mathbf{K} = 0$ $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy supercell eigenstates $|m\rangle$, having energies E_m , as [55,56]

$$G_n(E) = \sum_m \sum_{k=1}^{g(E_n^{(0)})} f_{n,mk} T(E_m - E), \quad (3)$$

where $g(E_n^{(0)})$ is the degeneracy of the Ge eigenstate $|n^{(0)}\rangle$, $T(E_m - E)$ is a so-called “top-hat” filter having unit height for $E = E_m$, being otherwise zero, and $f_{n,mk} = |\langle n^{(0)} | m \rangle|^2$ is the squared projection of the alloy supercell eigenstate $|m\rangle$ onto the Ge reference eigenstates $|n^{(0)}\rangle$. By computing $G_n(E)$ for a series of Ge eigenstates it is possible for a given alloy supercell to explicitly identify the composition of each individual alloy eigenstate as a linear combination of the eigenstates of the Ge host matrix semiconductor. This allows direct interrogation of alloy band hybridization effects and, undertaken as a function of alloy composition, enables the evolution of the alloy electronic structure to be quantified precisely [55,56]. Equation (3) defines a spectral function that is closely related to the $\mathbf{K} = 0$ contribution to the spectral function $A(\mathbf{k}, E)$ employed in our DFT effective band structure calculations [cf. Eq. (2)]. Here, $G_n(E)$ represents the contribution to the $\mathbf{K} = 0$ Bloch character associated with an individual Ge host matrix eigenstate $|n^{(0)}\rangle$ which is, in general, spread over several alloy supercell eigenstates $|m\rangle$ due to alloy-induced hybridization. Summing $G_n(E)$ over all Ge reference eigenstates $|n^{(0)}\rangle$

produces a spectral function representing the total Bloch character of all supercell eigenstates that backfold to $\mathbf{K} = 0$. In our TB analysis we compute and analyze $G_n(E)$ directly for individual Ge reference eigenstates, so as to explicitly quantify the contributions of individual Ge eigenstates to the hybridized $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy eigenstates.

IV. RESULTS

Interpretation of alloy electronic and optical properties is challenging due to breakdown of $\mathbf{k}$ selection associated with the reduction in translational symmetry arising from short-range alloy disorder and lattice relaxation. We therefore begin our discussion with the results of our small-supercell DFT and large-supercell TB electronic structure calculations in Secs. IV A and IV B, in order to inform the analysis of our PR and PL measurements in Secs. IV C and IV D. In Sec. IV E we compare our theoretical calculations and experimental measurements of the composition-dependent direct and indirect band gaps.

A. Density functional theory: Alloy effective band structures

The results of our effective band structure calculations for lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y/\text{Ge}$ 128-atom SQSs are summarized in Fig. 3. Here, the unfolded band structures are visualized in terms of their computed total Bloch character (spectral weight) $N(\mathbf{k}, E)$, which we have plotted on a logarithmic scale in order to emphasize features indicative of, and resulting from, alloy band mixing effects. These calculations reveal several key qualitative features of the electronic structure of lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y/\text{Ge}$ that are markedly different from the simplified description provided by the VCA.

The alloy CB structure is primarily Ge-like at low Si and Sn composition, with the CB minimum lying at the L point, but rapidly evolves to become Si-like with increasing Si and Sn composition, with the CB minimum lying approximately 80% of the way along the Δ direction between the Γ and X points. Beginning with a $\text{Si}_4\text{Ge}_{123}\text{Sn}_1$ ($x = 3.13\%$, $y = 0.78\%$) SQS in Fig. 3(a) we note that the band structure is qualitatively similar to that of Ge, but that even at this low Si composition the CB minimum along the Δ direction is lower in energy than the Γ -point CB edge. This band ordering is already similar to that of pure Si, where the Γ -point CB edge lies higher in energy than the CB edge states at the L and X points. As the Si and Sn compositions increase in Figs. 3(b)–(f) the magnitude of the calculated zero-temperature lowest-energy direct transition increases strongly, becoming equal to 1 eV by $x \approx 5.5\%$ [$y \approx 1.6\%$; cf. Fig. 3(b)]. Simultaneously, the minimum of the lowest-energy CB along the Δ direction is reduced in energy below the Γ -point CB edge. We note that our unfolded SQS band structures predict that lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y/\text{Ge}$ alloys retain an indirect fundamental band gap, in accordance with previous model estimates [3] and small supercell empirical pseudopotential calculations [14]. This behavior, which is in stark contrast to the emergence of a direct band gap in binary $\text{Ge}_{1-y}\text{Sn}_y$ alloys, is driven by the requirement to incorporate Si and Sn in the ratio 3.41:1 to maintain lattice matching to Ge or GaAs, with the impact of




FIG. 3. Effective (unfolded) alloy band structures, calculated via TB-mBJ DFT for relaxed 128-atom $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy supercells. The supercells contain (a) 1, (b) 2, (c) 3, (d) 4, (e) 5, and (f) 6 Sn atoms, with the corresponding number of Si atoms chosen in each case to achieve lattice matching to Ge ($x:y = 3.71:1$). The computed spectral weight N is depicted on a logarithmic scale, to emphasize the distribution of Bloch character over a significant wave vector and energy ranges for states lying close in energy to the CB minimum. The zero of energy is chosen to lie at the alloy VB edge for each supercell.

Si incorporation being to strongly reduce the energy of the Δ CB minimum relative to the zone-center CB edge [14]. At the highest Si and Sn compositions shown in Fig. 3, the $\text{Si}_{22}\text{Ge}_{100}\text{Sn}_6$ ($x = 17.19\%$, $y = 4.69\%$) SQS of Fig. 3(f), the zero-temperature band gap is ≈ 1.2 eV in magnitude, while the L and Δ CB minima are approximately equal in energy. At higher Si compositions (not shown) the Δ minima reduce in energy below the L -point CB edge, with the increasing X - L - Γ CB energy ordering then corresponding to that in pure Si for $x \gtrsim 20\%$ ($y \gtrsim 6\%$).

Additionally, with increasing Si and Sn composition we note the emergence of significant energetic broadening of the CB Bloch character. This behavior is characteristic of alloy disorder and band mixing effects. The reduction of translational symmetry due to chemical inhomogeneity and lattice relaxation means that the wave vector $\mathbf{k}$ is no longer a “good” quantum number (i.e., the crystal momentum is no longer a constant of carrier motion), with the resulting breakdown of $\mathbf{k}$ selection broadening the bands at fixed energy E . Additionally, this symmetry breaking ensures that orbital components of primitive cell $\mathbf{k}$ states having equivalent symmetry which fold back to the same supercell wave vector $\mathbf{K}$ can hybridize with one another. In the $4 \times 4 \times 4$ face-centered-cubic supercells considered here, the states which backfold to $\mathbf{K} = 0$ and can hence hybridize with Γ -point states are those having

primitive cell lattice vectors $\mathbf{k}$ whose components are integer multiples of $\frac{\pi}{2a}$ [20,57]. This includes L - and X -point states, so that our supercell calculations allow to track the band-gap evolution in the presence of alloy-induced band mixing between direct and indirect CB edge states. Hybridization between states which unfold from the same supercell wave vector $\mathbf{K}$ to different primitive wave vectors $\mathbf{k}$ are visible as “echoes” in $N(\mathbf{k}, E)$ at equal E and at the different $\mathbf{k}$ onto which the states unfold. This hybridization, combined with the loss of strict $\mathbf{k}$ selection, results in the distribution of Bloch character across the energies and wave vectors of the hybridizing states. This further drives energetic broadening of the alloy CB Bloch character, which is then enhanced in the presence of short-range alloy disorder. For example, in Figs. 3(e) and 3(f) the emergence of a Bloch character “tail” at Γ is visible at the same energies as the L - and X -point CB edge energies, reflecting that the loss of chemical and structural homogeneity drives hybridization between these states which acts to spectrally broaden the zone-center alloy CB edge.

The presence of such features in our effective band structure calculations reveals that alloy band mixing effects are present in $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys, being strongest close in energy to the CB edge, and hence that the direct alloy band gap is likely of hybridized character (being primarily indirect, but possessing an admixture of direct character) in the Ge-rich




FIG. 4. Calculated evolution of the configuration-averaged Ge L_{6c} (red), Γ_{7c} (green), and X_{5c} (blue) character of the CB states in disordered, 1024-atom $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy supercells lattice-matched to Ge ($x:y = 3.71:1$). (a) Illustrates for reference that the L -, Γ -, and X -point CB edge states in pure Ge, respectively, possess 100% Ge L_{6c} , Γ_{7c} , and X_{5c} character. Substitutional incorporation of Si and Sn [(b)–(h)] drives alloy-induced hybridization, with the CB states in Ge-rich alloys formed of an admixture of Ge host matrix CB states. The reduction in symmetry associated with short-range alloy disorder results in inhomogeneous energetic broadening of the associated direct (green) and indirect (red and blue) CB edges. The zero of energy is taken to lie at the Ge VB edge.

composition range under investigation [2,20,46]. Given the small separation in energy between L -, Γ -, and X -point CB edge states at these compositions, we expect that the hybridized zone-center alloy CB edge will be formed primarily of an admixture of the L_{6c} , Γ_{7c} , and X_{5c} CB edge states of Ge (cf. Sec. IV B). In several of the calculated effective band structures we note that while an accumulation of Γ -point CB Bloch character in a given energy range enables a direct band gap to be defined in principle, e.g., by weighting the energy of individual alloy CB states by their computed Bloch character [45], band mixing effects can lead to the emergence of Γ -point CB Bloch character at energies above and below the fundamental band gap. In this manner, alloy band mixing effects drive strong, inhomogeneous spectral broadening of the direct (optical, Γ -point) band gap. These qualitative features of the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ band structure are markedly distinct from the simplified interpretation offered by the VCA (and related approaches that neglect atomistic effects), highlighting that direct atomistic calculations are required to provide quantitative understanding of the nature and evolution of the strongly perturbed CB structure.

Conversely, the band structure close in energy to the VB edge remains predominantly Ge-like across the range of compositions studied here. Si (Sn) incorporation in Ge acts to decrease (increase) the VB spin-orbit splitting energy Δ_0 , with these effects approximately canceling one another when the Si to Sn composition ratio is chosen to maintain lattice matching to Ge, so that the alloy spin-orbit splitting energy remains approximately equal to that of Ge. Furthermore, compared to the calculated effective CB structure, we note minimal energetic broadening of the calculated Bloch character. This suggests that alloy band mixing effects have little impact on the band structure close in energy to the VB edge, similar to binary $\text{Ge}_{1-x}\text{Sn}_x$ alloys [20,45].

Overall, our DFT calculations (i) predict that lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y/\text{Ge}$ alloys retain an indirect fundamental band gap, and (ii) suggest that alloy band mixing

effects, akin to those recently identified in $\text{Ge}_{1-y}\text{Sn}_y$ [2,20,46], play an important role in determining the nature and evolution of the alloy CB structure. The observed energetic broadening of the CB Bloch character in purely substitutional (defect-free) alloy supercell calculations suggests that the optical absorption and emission spectra of $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ are predicted to be characterized by strong inhomogeneous spectral broadening. This spectral broadening, identified in our calculations as being driven by alloy-induced CB hybridization and enhanced by a loss of translational symmetry due to short-range alloy disorder, is expected to be an intrinsic property of $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys. To obtain a quantitative understanding of the evolution of the electronic structure requires the treatment of large-scale alloy supercells, for which we turn to a semiempirical approach.

B. Tight binding: Evolution of alloy band edge states

Figure 4 shows the TB-calculated Ge L_{6c} (red), Γ_{7c} (green), and X_{5c} (blue) character of the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy CB states as a function of composition for 1024-atom disordered alloy supercells. Here, the alloy CB L -, Γ -, and X -point CB character is computed using Ge_{1024} eigenstates $|n^{(0)}\rangle = |L_{6c}^{(0)}\rangle, |\Gamma_{7c}^{(0)}\rangle$, and $|X_{5c}^{(0)}\rangle$ in Eq. (3). For reference, Fig. 4(a) shows the calculated Ge L_{6c} , Γ_{7c} , and X_{5c} character in unperturbed Ge_{1024} . Here, the $\mathbf{K} = 0$ eigenstates form a complete orthonormal basis set, with $\langle m^{(0)} | n^{(0)} \rangle = \delta_{nm}$, so that Eq. (3) returns a value of unity at the energy $E_n^{(0)}$ of the reference Ge eigenstate $|n^{(0)}\rangle$. Results for alloy supercells in Figs. 4(b)–4(h) are obtained via configurational averaging: at each alloy composition we construct, relax, and compute the electronic structure of 25 distinct, randomly disordered supercells, and use the resulting alloy supercell eigenstates $|m\rangle$ in Eq. (3). Once the $G_n(E)$ spectra are computed for each of these 25 supercells, configurational averaging is performed by (i) accumulating the total Ge L_{6c} , Γ_{7c} , or X_{5c} character calculated for each individual supercell into energy bins of width 5 meV, and (ii) averaging

the total Ge L_{6c} , Γ_{7c} , or X_{5c} character accumulated in each of these energy bins for alloy 25 distinct disordered supercells considered at that composition. The resulting $G_n(E)$ spectra of Figs. 4(b)–4(h) provide detailed insight into the evolution of the alloy CB structure, effectively decomposing the calculated total Bloch character of the DFT unfolded alloy band structures of Fig. 3 into its distinct L -, Γ -, and X -point contributions.

Examining the evolution of the alloy CB structure described by Fig. 4, we first note a blueshift and energetic broadening of the L -point CB edge Bloch character with increasing Si and Sn composition. Across the composition range investigated, the alloy CB edge retains primarily indirect Ge L_{6c} character (red), but also acquires an admixture of direct Ge Γ_{7c} character (green). By comparison, we note that the energetic broadening of the Γ -point Bloch character due to alloy band mixing is significantly enhanced, with Ge Γ_{7c} character spread over an energy range extending upwards from the alloy CB edge by ~ 1 eV, even at low Si and Sn compositions $x = 4.00\%$ and $y = 1.07\%$ [cf. Fig. 4(c)]. We note that this is primarily driven by hybridization of Γ -point states with the large density of L -point states lying in the same energy range. Our calculations indicate that increasing the Si and Sn composition drives an admixture of Ge Γ_{7c} character to the alloy CB edge, while the majority of the calculated Ge L_{6c} character remains close in energy to the alloy CB edge, suggesting the presence of an indirect fundamental band gap. Finally, we note that the evolution of the X -point Bloch character is qualitatively similar to the L -point character, albeit redshifting in energy with increasing Si and Sn composition. The calculated Ge X_{5c} character also undergoes inhomogeneous energetic broadening with increasing Si and Sn composition, although in a less pronounced manner than that computed for the Γ_{7c} character.

As suggested by our DFT-calculated effective alloy band structures, our large-supercell TB calculations confirm that Si and Sn incorporation in Ge to form ternary $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys primarily and strongly impacts the CB structure, with the VB structure remaining comparatively unperturbed (and, for lattice-matched compositions, quantitatively close to that of the Ge host matrix semiconductor). This was verified via additional TB calculations of the alloy VB maximum (Ge Γ_{8v}) and spin-split-off VB edge (Ge Γ_{7v}) character which, compared to the calculated CB character of Fig. 4, were found to undergo minimal energy shifts or energetic broadening [30].

Having tracked the evolution of the CB and VB edge states in lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ via atomistic electronic structure calculations, we turn our attention now to elucidating the implications of our calculations for the nature and evolution of the alloy band gap. The strong inhomogeneous energetic broadening of Ge CB character across a multiplicity of hybridized alloy CB states complicates interpretation of the alloy band gap, and hence comparison between theoretical calculations and experimental measurements. To facilitate comparison to experiment, we use the $G_n(E)$ spectra of Fig. 4 to compute the weighted average energy associated with the Ge L_{6c} -, Γ_{7c} -, and X_{5c} -like alloy CB states and, in this manner, compute the composition-dependent band gaps that the associated indirect or direct optical transitions can be expected to track in experiment. We define this weighted average energy

as

$$\langle E_n \rangle = \sum_m \sum_{k=1}^{g(E_n^{(0)})} f_{n,mk} E_m, \quad (4)$$

where we use the Ge $|n^{(0)}\rangle$ character of each individual alloy supercell eigenstate $|m\rangle$ as the weight for the latter state's energy [cf. Eq. (3) and Fig. 4]. We note that Eq. (4) is properly normalized due to the fact that the $\mathbf{K} = 0$ eigenstates $\{|n^{(0)}\rangle\}$ and $\{|m\rangle\}$ of the Ge and $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ supercells form complete basis sets, so that the weights $f_{n,mk}$ sum to unity. As a consequence of the spectral theorem, Eq. (4) is equivalent to the matrix element $\langle n^{(0)} | \hat{H}(x, y) | n^{(0)} \rangle$ taken using the Ge host matrix supercell eigenstate $|n^{(0)}\rangle$, and the Hamiltonian $\hat{H}(x, y)$ of the Si- and Sn-containing alloy supercell.

Using Eq. (4) therefore allows to compute averaged Si and Sn composition-dependent shifts to the alloy Γ -, L -, and X -point CB edge energies, which correspond, respectively, to the weighted average energies associated with the Ge Γ_{7c} , L_{6c} , and X_{5c} character distributions shown in green, red, and blue in Fig. 4. Applying the same procedure to compute the Ge Γ_{8v} (HH/LH) and Γ_{7v} (SO) character allows us to track the evolution of the alloy VB states, and hence to compute the evolution of the direct and indirect alloy band gaps with composition for comparison to experiment in Sec. IV E, below.

C. Photorefectance: Evolution of direct band gap

The open black circles in Fig. 5(a) show the measured PR spectrum for a pure Ge (substrate) reference sample. We note the presence of a critical point feature with a sharp minimum at energy ≈ 0.8 eV, and an additional feature at ≈ 1.1 eV, which correspond, respectively, to the expected direct Γ_{7c} - Γ_{8v} (CB-VB) transition at energy E_0 , and the Γ_{7c} - Γ_{7c} (CB-SO) interband transition at energy $E_0 + \Delta_0$ [27]. These data were fitted using Eq. (1) (solid black line), including critical points for E_0 and $E_0 + \Delta_0$ transitions, as well as the excitonic contribution at energy E_{ex} close to E_0 . Previously reported exciton binding energy values for Ge are close to 2 meV [63], and so the exciton binding energy was fixed to this value during the fit, i.e., $E_{\text{ex}} - E_0 = -2$ meV. The individual CB-VB, excitonic, and CB-SO contributions to the total PR fit are respectively shown in Fig. 5(a) using solid red, green, and blue lines.

Fitting of the features corresponding to the lowest-energy direct transition in the measured PR spectra for the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples was performed using the combined interference/critical point model described in Sec. II B, to account for thin-film interference effects in addition to changes in reflectance associated with the critical point feature of interest. Open black circles and solid black lines in Fig. 5, respectively, show the measured PR spectra and best model fit for the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples (b) A1, (c) B2 (thick), and (d) B3 (thin). The combined critical point/interference model was fit using a differential evolution algorithm and, due to the large number of model parameters, running the model multiple times produced slightly different results. However, the key parameters of interest (E_0 and Δ_0) were found to display minimal variation across multiple runs of the fitting algorithm [30]. Again, the CB-VB, excitonic, and CB-SO




FIG. 5. Measured (open black circles) and fitted (solid black lines) low-energy PR spectra for (a) a Ge reference sample and samples (b) A1, (c) B2 (thick), and (d) B3 (thin) (cf. Table I). The left- and right-hand vertical arrows, respectively, denote the E_0 and $E_0 + \Delta_0$ transition energies extracted based on the PR fit. The data for Ge were fitted directly to Eq. (1), while fits to the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ data were performed using the combined interference/critical point model described in Sec. II B. Dashed red, green, and blue lines, respectively, show the best-fit 3D M_0 -type E_0 (CB-VB), excitonic, and $E_0 + \Delta_0$ (CB-SO) contributions to the PR fits. Dashed black lines show the thin-film interference contribution to the PR fits for the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ data.

contributions to the overall fit are shown using solid red, green, and blue lines for each alloy sample in Figs. 5(b)–5(d), while dashed black lines show the contribution to $\frac{\Delta R}{R}$ due to thin-film interference. The best-fit values of E_0 and Δ_0 for all samples are listed in Table II. The direct transition energy E_0 was observed to blueshift strongly with increasing Si and

Sn composition, while the VB spin-orbit splitting energy Δ_0 remains close to the value 0.308 eV measured for pure Ge. For sample set B, the measured PR data for the “thick” and “thin” samples were fitted to independently, yet yielded the same average E_0 energy to within 4 meV. This confirms that the samples have nominally equal Si and Sn compositions at different thicknesses (cf. Table I), as expected based on structural characterization experiments [23]. In addition, the best-fit E_0 values are in good quantitative agreement with values obtained via spectroscopic ellipsometry measurements performed on the same set of samples [23].

D. Photoluminescence: Evolution of indirect band gap

PL spectra for the six $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy samples are shown in Figs. 6(b) and 6(c), where measured PL spectra for sample set B are shown only for the thicker samples due to their observed higher luminescence intensity. The presence of multiple peaks in the measured power-dependent PL spectra for each sample, fitted as shown in Fig. 7, hinders the straightforward determination of the indirect band gap from the PL data. The origin of these peaks could be phonon-assisted emission involving either L - or X -point CB and Γ -point VB states (akin respectively to the fundamental band gap of Ge or Si), or direct Γ -point transitions (akin to the direct Γ_{7c} - Γ_{8v} transition in Ge). Also possible are peaks corresponding to the spectral broadening of the emission spectra predicted by our large-supercell TB calculations of the alloy CB state character, as well as recombination involving localized states associated

TABLE II. Direct transition energy E_0 and VB spin-orbit splitting energy Δ_0 extracted from fits to measured room-temperature PR spectra, and fundamental (indirect) band gap E_{ind} extracted from fits to measured room-temperature PL spectra. Listed values of E_0 and Δ_0 are averages obtained from 10 different runs of the PR fitting algorithm [30]. Listed uncertainties are the associated standard deviations. PL measurements were performed only for the “thick” ($d \approx 2 \mu\text{m}$) samples from set B (cf. Table I).

Sample	PR E_0 (eV)	PR Δ_0 (eV)	PL E_{ind} (eV)
Ge	0.807	0.308	0.666
A1	0.941 ± 0.007	0.28 ± 0.01	0.705
A2	1.000 ± 0.020	0.27 ± 0.02	0.713
A3	1.010 ± 0.002	0.30 ± 0.01	0.745
B1 (thin)	0.870 ± 0.006	0.29 ± 0.01	
B1 (thick)	0.870 ± 0.003	0.29 ± 0.01	0.690
B2 (thin)	0.910 ± 0.003	0.30 ± 0.01	
B2 (thick)	0.910 ± 0.020	0.29 ± 0.01	0.711
B3 (thin)	0.950 ± 0.010	0.29 ± 0.01	
B3 (thick)	0.950 ± 0.008	0.30 ± 0.01	0.726




FIG. 6. Measured PL spectra of (a) Ge, (b) $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy sample set A, and (c) $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy sample set B, at low (dashed lines) and high (solid lines) incident laser power. In (b) and (c) green, blue, and purple lines, respectively, show the measured PL spectra in order of increasing Si and Sn composition (cf. Table I). The spectra for the medium and high composition samples are, respectively, rigidly shifted by +0.5 and +1, to enhance visibility. In (c), measurements are shown only for “thick” set B samples. All PL spectra are normalized with respect to their peak luminescence intensity.

with native defects. Contributions to the PL spectra of a given sample are also likely to consist of several distinct peaks corresponding to different phonon-assisted transitions, as is the case for Ge [cf. Fig. 6(a) and Ref. [35]]. Here, the power dependence of the observed room-temperature PL indicates that it is due to emission from the bulk rather than localized features or defects [30]. Our theoretical calculations indicate

that, across the composition range under investigation, the Si-like $X_{5c}-\Gamma_{8v}$ transition energy of $\gtrsim 1$ eV is significantly higher than the direct E_0 transition, making it unlikely that this transition contributes significantly to the PL of any of the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples.

Thus, the most likely origin of the multiple PL peaks in the measured $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ room-temperature PL spectra is




FIG. 7. Illustration of the fits to the PL data at low power using Gaussian and Lorentzian line shapes. The total fit to the data and individual peaks are shown for (a) the Ge reference sample, (b) sample A2, and (c) the thicker B3 sample. The arrows indicate the individual peak locations; the red arrow in each case indicates the peak with the highest intensity, which was taken to correspond to LA phonon absorption by analogy with the PL spectrum of Ge.

different phonon-assisted $L_{6c}-\Gamma_{8v}$ recombination processes, in combination with emission from the direct $\Gamma_{7c}-\Gamma_{8v}$ gap, with the latter appearing as a high-energy tail. For the indirect gap emission processes we do not expect that any individual PL peak energy corresponds directly to the fundamental band gap, as the energies of these features will be offset by the energy of the emitted or absorbed phonon, with the observed phonon-assisted PL peak energy being lower (higher) in energy than the associated indirect band gap for a transition assisted by phonon emission (absorption). There is therefore some difficulty in associating the observed low-energy PL peaks directly to specific phonon modes, first since the loss of translational symmetry in the alloy removes the requirement to conserve crystal momentum, allowing a large number of phonon modes to contribute to indirect recombination, and, second, due to a lack of information on how phonon energies vary in disordered $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys compared to Ge. Overall, we note that there does not appear to be a direct correspondence between the measured energy offsets between the phonon-assisted PL peak energies and associated indirect fundamental band gap for the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy samples compared to the Ge reference sample. This makes it challenging to associate specific phonon modes to observed indirect PL peaks. Therefore, the room-temperature band gap of the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ samples was estimated by identifying the highest-intensity peak in the Ge room-temperature PL spectrum, which corresponds to an indirect $L_{6c}-\Gamma_{8v}$ transition assisted by absorption of a longitudinal acoustic phonon having energy 27 meV [22]. In order to consistently estimate the fundamental indirect band-gap energy, it was assumed that the highest-intensity peak in the measured PL spectrum for each $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ sample was also associated with absorption of a phonon of energy 27 meV. The resulting estimated indirect band gaps are listed in Table II, and plotted in Fig. 8(b) using closed red squares, demonstrated a linear blueshift with increasing Si and Sn composition.

E. Theory vs experiment: Direct and indirect band gaps

The results of our PR (closed green diamonds) and PL (closed red squares) measurements of the direct and indirect band gaps are summarized in Fig. 8(b). Following the procedure described in Sec. IV B, we have used the TB method to compute the composition dependence of the weighted average direct and indirect band gaps of lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$. The results of these calculations are shown in Fig. 8(b) using open triangles for the direct $\Gamma_{7c}-\Gamma_{8v}$ (green), and indirect $L_{6c}-\Gamma_{8v}$ (red), and $X_{5c}-\Gamma_{8v}$ (blue) band gaps. In order to compare our zero-temperature theoretical calculations and room-temperature experimental measurements, we have rigidly redshifted the calculated band gaps so that the calculated direct $\Gamma_{7c}-\Gamma_{8v}$ band gap of Ge aligns with the value of 0.807 eV extracted from our PR measurements (cf. Table II). Applying this same redshift rigidly to all calculated band gaps then allows the predicted composition dependence to be quantitatively compared to experiment.

In comparing our theoretical calculations and experimental measurements, we note three important considerations. First, our theoretical calculations are for nominally lattice-matched alloy supercells, where the supercell lattice constant




FIG. 8. (a) SEM-EDX measured Si to Sn composition ratios $x:y$ for the samples investigated (cf. Table I). (b) Comparison of the transition energies extracted from experimental measurements (points) and calculated using TB method (lines), showing data for the indirect band gap from PL measurements (red squares), and for the direct transition from PR measurements (green diamonds). The theoretical results are the calculated weighted average direct $\Gamma_{7c}-\Gamma_{8v}$ (green), and indirect $L_{6c}-\Gamma_{8v}$ (red) and $X_{5c}-\Gamma_{8v}$ (blue) transition energies.

conforms very closely to that Ge, while our CVD-grown samples possess composition ratios which deviate from the ideal lattice-matched Si to Sn composition ratio, as shown in Fig. 8(a). As a result, a given Si composition in Fig. 8(b) does not imply equal Sn compositions in theory and experiment. The measured lattice constants for these samples suggest lattice mismatch of $\leq 0.03\%$ with respect to Ge [23], and thus strain is not expected to impact the measured transition energies. Second, we recall that the CB and VB energies used to calculate the theoretical transition energies are computed as a weighted average of the distribution of the corresponding Ge Γ -, L -, or X -point Bloch character over individual alloy supercell states. These weighted average energy gaps therefore display virtual crystal-like behavior, i.e., approximately linear variation with composition, with bowing of individual state energies averaged out, which can only be expected to describe the composition dependence of a given transition energy on

average in terms of its contributions from a multiplicity of states possessing an admixture of Γ , L , or X character and spread over a range of energies in the alloy band structure. As described in Sec. III, the allowed band mixing in a given alloy supercell is determined in part by the supercell size, which controls the number of states that fold to a given supercell wave vector $\mathbf{K}$. We therefore expect that our calculated weighted average band gaps will tend to overestimate the corresponding transition energies measured in experiment since only a limited number of states fold back to $\mathbf{K} = 0$ close in energy to the CB edge in a given alloy supercell. Third, as discussed in Sec. IV D, the presence of multiple peaks in the PL spectra, associated with different phonon-assisted emission pathways, means there is uncertainty associated assigning a single energy to the measured indirect fundamental band gap.

Bearing these potential sources of error in mind, we nonetheless note good overall agreement between theory and experiment in Fig. 8(b). Our calculated increase of 28.4 meV per % Si of the direct Γ_{7c} - Γ_{8v} transition (open red triangles) corresponds well to the E_0 values extracted from the PR measurements (closed red diamonds) for samples A1, A2, and B1, but overestimates the direct transition energy measured for samples A3, B2, and B3. Similarly, our calculated increase of 14.1 meV per % Si of the indirect L_{6c} - Γ_{8v} band gap slightly overestimates, but corresponds well to, the fundamental band gap identified from our PL measurements. As predicted by theory, the VB spin-orbit splitting energy Δ_0 does vary significantly across the composition range. Based on this analysis we conclude that lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ retains an indirect fundamental band gap, associated primarily with an L -point CB minimum, albeit with theoretical calculations suggesting that band hybridization effects result in this fundamental band gap having a hybridized nature, possessing an admixture of Ge Γ_{7c} character that should allow for (weak, spectrally broad) optical absorption at energies below the weighted average direct band gap indicated in Fig. 8. Finally, our calculated reduction of 4.6 meV per % Si for the X_{5c} - Γ_{8v} band gap results in a crossover from L - Γ - X to L - X - Γ CB edge energy ordering for $x \gtrsim 7.5\%$. We note that this is predicted to occur in the composition range in which the direct E_0 transition is close to 1 eV in magnitude at room temperature, in accordance with the band ordering identified in our DFT effective band structure calculations (cf. Fig. 3).

For multijunction solar-cell applications, the indirect nature of the fundamental band gap of $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys having a direct Γ_{7c} - Γ_{8v} transition energy close to 1 eV ($x \approx 8.0\%$, $y \approx 2.2\%$) is expected to have a detrimental impact on the cell voltage. For application as a 1-eV junction, where lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ is grown epitaxially with thicknesses up to several μm , the direct Γ_{7c} - Γ_{8v} transition will dominate the optical absorption. This offers advantages for current matching in three- or four-junction solar cells compared to a cell having a pure Ge junction. However, the presence of the lower-energy indirect L_{6c} - Γ_{8v} band gap will allow carriers to thermalize to lower-energy CB states after being absorbed across the Γ_{7c} - Γ_{8v} transition, thus reducing the voltage that can be extracted from the cell compared to a material having a 1-eV direct fundamental band gap. Nonetheless, since the fundamental indirect band gap is increased in lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ compared to that

of Ge, $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ subcells should be able to achieve a higher voltage, and thus an overall improved triple-junction cell efficiency, compared to an equivalent cell employing a pure Ge junction.

V. CONCLUSIONS

In summary, we have presented a combined experimental and theoretical analysis of ternary $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys lattice-matched to Ge and GaAs. Our experimental measurements quantified the evolution of the optical properties with alloy composition, focusing on trends in the direct and indirect band gaps, while our theoretical calculations elucidated these trends in terms of the evolution of the alloy electronic structure. Our results provide insight into the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloy band structure, demonstrating that its evolution is characterized primarily by a perturbed CB structure that undergoes rapid change with increasing Si and Sn composition.

Experimentally, we reported room-temperature PR and PL spectroscopic measurements, which were respectively employed to track the evolution of the direct and indirect band gaps as a function of alloy composition. Theoretically, we reported first-principles and semiempirical calculations of the alloy electronic structure. Effective (unfolded) first-principles band structure calculations for lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ highlighted the presence of Si- and Sn-induced alloy band mixing, similar to that observed in recent calculations for binary $\text{Ge}_{1-y}\text{Sn}_y$ alloys. We predicted theoretically and confirmed via photoluminescence measurements that lattice-matched $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys retain an indirect fundamental band gap, and further identified that the electronic structure evolution at low Si and Sn composition is strongly influenced by the impact of alloy band mixing on the CB. This alloy band mixing, combined with a breakdown in $\mathbf{k}$ selection due to a loss of translational symmetry in a disordered alloy, generates significant energetic broadening of CB edge states. Large-scale semiempirical calculations further elucidated this behavior, demonstrating that alloying results in a distribution of direct-gap (Ge Γ_{7c}) character across a multiplicity of alloy CB states. Taken together, our theoretical calculations and experimental measurements suggest that the observed strong inhomogeneous broadening of optical spectra is then an intrinsic property of substitutional $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys. Our experimental measurements and theoretical calculations confirm the previously demonstrated blueshift of the direct band gap with increasing Si composition, suggesting that it increases at a rate of ≈ 28 meV per % Si in a lattice-matched alloy.

Our results confirm that $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys lattice-matched to Ge possess an indirect fundamental band gap which, for $E_0 \approx 1$ eV, lies 250–300 meV below the Γ_{7c} - Γ_{8v} transition in energy, which theoretical calculations identify as resulting from alloy CB edge states being primarily derived from the L_{6c} CB minimum of the Ge host matrix semiconductor. While the presence of an indirect fundamental band gap is expected to adversely affect the voltage of a $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ solar cell compared to a material having a 1-eV direct band gap, the improved potential for current matching in lattice-matched architectures and an expected increase in voltage

compared to an equivalent Ge cell make $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ alloys a promising candidate material for multijunction solar cells.

ACKNOWLEDGMENTS

This work was supported by the Engineering and Physical Sciences Research Council, U.K. (EPSRC; via a CASE Studentship, held by P.P. and sponsored by IQE plc.), by the National University of Ireland (NUI; via the Post-Doctoral

Fellowship in the Sciences, held by C.A.B.), by Science Foundation Ireland (SFI; Project No. 15/IA/3082), and by the Royal Society (via an Industry Fellowship, held by N.J.E.-D.). This work was carried out in part during research visits to Imperial College London, U.K., by C.A.B., supported by a Charlemont Grant from the Royal Irish Academy. The authors thank S. W. Ong (National University of Singapore) for performing the SEM-EDX composition measurements.

- [1] S. Wirths, D. Buca, and S. Mantl, *Prog. Cryst. Growth Charact. Mater.* **62**, 1 (2016).
- [2] O. Moutanabbir, S. Assali, X. Gong, E. P. O'Reilly, C. A. Broderick, B. Marzban, J. Witzens, W. Du, S.-Q. Yu, A. Chelnokov *et al.*, *Appl. Phys. Lett.* **118**, 110502 (2021).
- [3] G. Sun, R. A. Soref, and H. H. Cheng, *J. Appl. Phys.* **108**, 033107 (2010).
- [4] Y. Zhou, J. Margetis, G. Abernathy, W. Dou, P. C. Grant, B. Alharthi, W. Du, A. Wadsworth, Q. Guo, H. Tran *et al.*, in *Proceedings on the Conference on Lasers and Electro-Optics (CLEO)* (IEEE, Piscataway, NJ, 2019).
- [5] R. T. Beeler, J. Gallagher, C. Xu, L. Jiang, C. L. Senaratne, D. J. Smith, J. Menéndez, A. V. G. Chizmeshya, and J. Kouvetakis, *ECS J. Solid State Sci. Technol.* **2**, Q172 (2013).
- [6] N. von den Driesch, D. Stange, S. Wirths, D. Rainko, I. Povstugar, A. Savenko, U. Breuer, R. Geiger, H. Sigg, Z. Ikonik *et al.*, *Small* **13**, 1603321 (2017).
- [7] Y.-Y. Fang, J. Xie, J. Tolle, R. Roucka, V. R. D'Costa, A. V. G. Chizmeshya, J. Menéndez, and J. Kouvetakis, *J. Am. Chem. Soc.* **130**, 16095 (2008).
- [8] C. I. V. L., J. D. Querales Flores, J. D. Fuhr, and R. A. Barrio, *Prog. Photovolt.: Res. Appl.* **23**, 112 (2015).
- [9] R. Roucka, A. Clark, T. Wilson, T. Thomas, M. Führer, N. J. Ekins-Daukes, A. D. Johnson, R. Hoffman, and D. Begarney, *IEEE J. Photovolt.* **6**, 1025 (2016).
- [10] R. T. Beeler, D. J. Smith, J. Kouvetakis, and J. Menéndez, *IEEE J. Photovolt.* **2**, 434 (2012).
- [11] S. Wirths, A. T. Tiedemann, Z. Ikonik, P. Harrison, B. Holländer, T. Stoica, G. Mussler, M. Myronov, J. M. Hartmann, D. Grützmacher *et al.*, *Appl. Phys. Lett.* **102**, 192103 (2013).
- [12] S. Sant and A. Schenk, *IEEE J. Electron. Devices Soc.* **3**, 164 (2015).
- [13] R. R. King, A. Boca, W. Hong, X. Q. Liu, D. Bhusari, D. Larrabee, K. M. Edmondson, D. C. Law, M. Fetzer, S. Mesropian *et al.*, in *24th European Photovoltaic Solar Energy Conference and Exhibition* (WIP Renewable Energies, Munich, 2009), pp. 1–7.
- [14] P. Moontragoon, R. A. Soref, and Z. Ikonik, *J. Appl. Phys.* **112**, 073106 (2012).
- [15] T. Wendav, I. A. Fischer, M. Montanari, M. H. Zoellner, W. Klesse, G. Capellini, N. von den Driesch, M. Oehme, D. Buca, K. Busch *et al.*, *Appl. Phys. Lett.* **108**, 242104 (2016).
- [16] P. Aella, C. Cook, J. Tolle, S. Zollner, A. V. G. Chizmeshya, and J. Kouvetakis, *Appl. Phys. Lett.* **84**, 888 (2004).
- [17] R. Soref, J. Kouvetakis, J. Tolle, J. Menéndez, and V. D'Costa, *J. Mater. Res.* **22**, 3281 (2007).
- [18] A. Zunger, S.-H. Wei, L. G. Ferreira, and J. E. Bernard, *Phys. Rev. Lett.* **65**, 353 (1990).
- [19] S.-H. Wei, L. G. Ferreira, J. E. Bernard, and A. Zunger, *Phys. Rev. B* **42**, 9622 (1990).
- [20] E. J. O'Halloran, C. A. Broderick, D. S. P. Tanner, S. Schulz, and E. P. O'Reilly, *Opt. Quantum Electron.* **51**, 314 (2019).
- [21] L. Vegard, *Z. Phys.* **5**, 17 (1921).
- [22] *Group IV Elements, IV-IV and III-V Compounds. Part B - Electronic, Transport, Optical and Other Properties*, Landolt-Börnstein-Group III Condensed Matter, edited by O. Madelung, U. Rössler, and M. Schulz (Springer, Berlin, 2002).
- [23] P. Pearce, Novel materials and device architectures for high-efficiency solar cells, Ph.D. thesis, Imperial College London, 2021, <https://doi.org/10.25560/88448>.
- [24] *Semiconductor Research*, Springer Series in Materials Science, edited by A. Patané and N. Balkan (Springer, Berlin, 2012), Vol. 150.
- [25] P. M. Amirtharaj, D. Chandler-Horowitz, and D. P. Bour, *MRS Proc.* **406**, 229 (1995).
- [26] D. E. Aspnes, *Surf. Sci.* **37**, 418 (1973).
- [27] S. Adachi, *Phys. Rev. B* **38**, 12966 (1988).
- [28] V. R. D'Costa, C. S. Cook, A. G. Birdwell, C. L. Littler, M. Canonico, S. Zollner, J. Kouvetakis, and J. Menéndez, *Phys. Rev. B* **73**, 125207 (2006).
- [29] H. Shen and M. Dutta, *J. Appl. Phys.* **78**, 2151 (1995).
- [30] See Supplemental Material at <http://link.aps.org/supplemental/10.1103/PhysRevMaterials.6.015402> which includes Refs. [64–68], for (1) details of the model used to fit the photoreflectance data, (2) additional data from power-dependent photoluminescence measurements, (3) estimates of sample heating due to laser exposure, (4) details of the model used to fit the photoluminescence data, and (5) details of the character of the $\text{Si}_x\text{Ge}_{1-x-y}\text{Sn}_y$ valence band from tight-binding calculations.
- [31] D. Huang, D. Mui, and M. Morkoç, *J. Appl. Phys.* **66**, 358 (1989).
- [32] N. Kallergi, B. Roughani, J. Aubel, and S. Sundaram, *J. Appl. Phys.* **68**, 4656 (1990).
- [33] S. Ghosh and B. M. Arora, *J. Appl. Phys.* **81**, 6968 (1997).
- [34] D. Alonso-Álvarez, T. Wilson, P. Pearce, M. Führer, D. Farrell, and N. J. Ekins-Daukes, *J. Comput. Electron.* **17**, 1099 (2018).
- [35] R. R. Lietaen, K. Bustillo, T. Smets, E. Simoen, J. W. Ager, III, E. E. Haller, and J.-P. Locquet, *Phys. Rev. B* **86**, 035204 (2012).
- [36] F. Tran and P. Blaha, *Phys. Rev. Lett.* **102**, 226401 (2009).
- [37] P. E. Blöchl, *Phys. Rev. B* **50**, 17953 (1994).
- [38] G. Kresse and D. Joubert, *Phys. Rev. B* **59**, 1758 (1999).
- [39] G. Kresse and J. Furthmüller, *Comput. Mater. Sci.* **6**, 15 (1996).
- [40] G. Kresse and J. Furthmüller, *Phys. Rev. B* **54**, 11169 (1996).
- [41] D. S. P. Tanner, C. A. Broderick, A. C. Kirwan, S. Schulz, and E. P. O'Reilly, Fully analytic valence force fields for

- the relaxation of group-IV semiconductor alloys: elastic properties of group-IV materials calculated from first principles, [arXiv:2110.11888](#).
- [42] B. L. Booth and A. W. Ewald, *Phys. Rev.* **168**, 796 (1968).
 - [43] S. H. Groves, C. R. Pidgeon, A. W. Ewald, and R. J. Wagner, *J. Phys. Chem. Solids* **31**, 2031 (1970).
 - [44] P. Moontragoon, Z. Ikonić, and P. Harrison, *Semicond. Sci. Technol.* **22**, 742 (2007).
 - [45] C. O'Donnell, A. Sanchez-Soares, C. A. Broderick, and J. C. Greer, *J. Phys. D: Appl. Phys.* **54**, 245103 (2021).
 - [46] T. D. Eales, I. P. Marko, S. Schulz, E. J. O'Halloran, S. Ghetmiri, W. Du, Y. Zhou, S.-Q. Yu, J. Margetis, J. Tolle *et al.*, *Sci. Rep.* **9**, 14077 (2019).
 - [47] A. van de Walle, M. Asta, and G. Ceder, *CALPHAD: Comput. Coupling Phase Diagrams Thermochem.* **26**, 539 (2002).
 - [48] A. van de Walle, *CALPHAD: Comput. Coupling Phase Diagrams Thermochem.* **33**, 266 (2009).
 - [49] A. van de Walle, P. Tiwarya, M. de Jong, L. Olmsted, A. Dick, D. Shin, Y. Wang, L.-Q. Chen, and Z.-K. Liu, *J. Calphad* **42**, 13 (2013).
 - [50] V. Popescu and A. Zunger, *Phys. Rev. Lett.* **104**, 236403 (2010).
 - [51] V. Popescu and A. Zunger, *Phys. Rev. B* **85**, 085201 (2012).
 - [52] P. V. C. Medeiros, S. Stafström, and J. Björk, *Phys. Rev. B* **89**, 041407(R) (2014).
 - [53] P. V. C. Medeiros, S. S. Tsirkin, S. Stafström, and J. Björk, *Phys. Rev. B* **91**, 041116(R) (2015).
 - [54] Y. Zhang and L.-W. Wang, *Phys. Rev. B* **83**, 165208 (2011).
 - [55] M. Usman, C. A. Broderick, A. Lindsay, and E. P. O'Reilly, *Phys. Rev. B* **84**, 245202 (2011).
 - [56] M. Usman, C. A. Broderick, and E. P. O'Reilly, *Phys. Rev. Appl.* **10**, 044024 (2018).
 - [57] C. A. Broderick, M. D. Dunne, D. S. P. Tanner, and E. P. O'Reilly, *J. Appl. Phys.* **126**, 195702 (2019).
 - [58] H.-S. Lan, S. T. Chang, and C. W. Liu, *Phys. Rev. B* **95**, 201201(R) (2017).
 - [59] M. P. Polak, P. Scharoch, and R. Kudrawiec, *J. Phys. D: Appl. Phys.* **50**, 195103 (2017).
 - [60] J. D. Gale, *JCS Faraday Trans.* **93**, 629 (1997).
 - [61] J. D. Gale and A. L. Rohl, *Mol. Simul.* **29**, 291 (2003).
 - [62] J. D. Gale, *Z. Kristallogr.* **220**, 552 (2005).
 - [63] Y. Yin, D. Yan, F. H. Pollak, M. S. Hybertsen, J. M. Vandenberg, and J. C. Bean, *Phys. Rev. B* **52**, 8951 (1995).
 - [64] S. Adachi, *Physical Properties of III-V Semiconductor Compounds* (Wiley, Weinheim, 2005), Vol. 783, pp. 135–192.
 - [65] W. Klingenstein and H. H. Schweizer, *Solid State Electron.* **21**, 1371 (1978).
 - [66] H. M. van Driel, A. Elci, J. S. Bessey, and M. O. Scully, *Solid State Commun.* **20**, 837 (1976).
 - [67] T. Schmidt, K. Lischka, and W. Zulehner, *Phys. Rev. B* **45**, 8989 (1992).
 - [68] F. Rathgeber, D. A. Ham, L. Mitchell, M. Lange, F. Luporini, A. T. T. Mcrae, G.-T. Bercea, G. R. Markall, and P. H. J. Kelly, *ACM Trans. Math. Software* **43**, 24 (2016).