

Title	A regrowth-free, facetless multiple quantum wells AlInGaAs semiconductor laser suitable for photonic integration
Authors	Caro, Ludovic;Yang, Hua;Peters, Frank H.;Dernaika, Mohamad
Publication date	2018-07
Original Citation	Dernaika, M., Caro, L., Yang, H. and Peters, F. H. (2018) 'A regrowth-free, facetless multiple quantum wells AlInGaAs semiconductor laser suitable for photonic integration', Proceedings of Advanced Photonics Congress 2018, Zurich, Switzerland, 2-5 July, ITu4B.3 (2pp). doi:10.1364/ IPRSN.2018.ITu4B.3
Type of publication	Conference item
Link to publisher's version	http://www.osapublishing.org/abstract.cfm?URI=IPRSN-2018- ITu4B.3 - 10.1364/IPRSN.2018.ITu4B.3
Rights	© 2018, the Authors. Published by the Optical Society of America. One print or electronic copy may be made for personal use only. Systematic reproduction and distribution, duplication of any material in this paper for a fee or for commercial purposes, or modifications of the content of this paper are prohibited.
Download date	2025-04-06 12:37:50
Item downloaded from	https://hdl.handle.net/10468/7671



University College Cork, Ireland Coláiste na hOllscoile Corcaigh

A regrowth-free, facetless multiple quantum wells AlInGaAs semiconductor laser suitable for photonic integration

Mohamad Dernaika^{1,2}, Ludovic Caro^{1,3}, Hua Yang¹ and Frank H. Peters^{1,3}

¹Integrated Photonics Group, Tyndall National Institute, Dyke Parade, Cork, Ireland. ²Electrical and Electronic Engineering Department, University College Cork, College Road, Cork, Ireland ³Physics Department, University College Cork, College Road, Cork, Ireland mohamad.dernaika@tyndall.ie

Abstract: A facetless, semiconductor laser suitable for photonic integration is presented in this paper. The laser fabrication process employs contact lithography and regrowth-free process. Moreover, the laser cavity is monolithically integrated with a semiconductor optical amplifier. © 2018 The Author(s)

OCIS codes: 250.5300, 250.5960, 110.5220, 140.3410,

1. introduction

Photonic integrated circuits (PIC) based on active InP provide a variety of photonic building blocks that cannot be implemented in passive material. However, InP PICs lack the leverage of the existing micro-electronic infrastructure and silicon photonics industry. Thus, their commercial use is limited by economic factors, such as effective mass production, lead time and fabrication complexity.

As a result, a generic InP integration technology initiative to share the cost between interested parties has been developed in order to push the industry forward [1]. At this stage, further cost reduction, shorter processing times, and simplified fabrication processes are still necessary to extend the industry to the next level to encourage more commercial use. Laser cavities that can be fabricated with contact lithography and regrowth-free processes drastically reduce the overall time and cost of the fabrication process. These lasers have attracted considerable interest due to their relatively simple fabrication process and have demonstrated great potential as cost effective tunable laser sources for telecommunication applications [2].

In this paper, we present a facetless semiconductor laser suitable for photonic integration fabricated using contact UV lithography in a regrowth-free process. The laser cavity consists of 2 higher order grating pit mirrors coupled to an active ring resonator via a half-wave coupler (HWC) [3].




Fig. 1. Laser cavity design

2. Cavity fabrication and design

The laser was fabricated using standard n-doped multiple quantum well epitaxial wafers purchased from IQE. Four lithography steps were used to define the ridge, etch depth, metal opening, and metal lift-off. Top p-metal and back side n-metal was 20:500 Ti:Au and 20:300 Ti:Au respectively.

The laser cavity design is shown in Fig.1. Two pit mirrors [4] are used to create a narrow bandwidth resonator, and the light from this cavity is then coupled to a ring laser via a HWC. These coupled resonators enhance and amplify the desired mode while suppressing the remainder. Laser emission is coupled to a waveguide that acts as a semiconductor optical amplifier (SOA) and an output waveguide. The output is then coupled to an optical spectrum analyzer via a lensed fibre.




Fig. 2. (a) single mode output, (b) continuous tuning across 4 nm

Fig.2 (a) shows the single mode output of the laser, while Fig.2 (b) shows a fine tuning example of laser, which can continuously cover around 4 nm by changing the injected current into the different sections of the cavity. The single mode showed a 0.098nm/degree shift over a 15 degrees increase in temperature, without any mode hopping.

References

- Smit, M., Leijtens, X., Ambrosius, H., Bente, E., Van der Tol, J., Smalbrugge, B., De Vries, T., Geluk, E.J., Bolk, J., Van Veldhoven, R. and Augustin, L., 2014. An introduction to InP-based generic integration technology. Semiconductor Science and Technology, 29(8), p.083001.
- Byrne, D.C., Engelstaedter, J.P., Guo, W.H., Lu, Q.Y., Corbett, B., Roycroft, B., O'Callaghan, J., Peters, F.H. and Donegan, J.F., 2009. Discretely tunable semiconductor lasers suitable for photonic integration. IEEE Journal of Selected Topics in Quantum Electronics, 15(3), pp.482-487.
- Lin, X., Liu, D. and He, J.J., 2009. Design and analysis of 2 × 2 half-wave waveguide couplers. Applied optics, 48 (25), pp.F18-F23.
- 4. Dernaika, M., Kelly, N.P., Caro, L., Shortiss, K. and Peters, F.H., 2017. Regrowth-free single-mode semiconductor laser suitable for monolithic integration based on pits mirror. Optical Engineering, **56**(8), p.086107.